

# AHMEDABAD TEXTILE INDUSTRY'S RESEARCH ASSOCIATION

P.O. Ambawadi Vistar, Ahmedabad-380 015. India.

Ph. : (079) 26307921-7922-7923-5131-32-33 (Extn. No. : 346) Fax : (079) 26304677

E-mail : [ttl@atira.in](mailto:ttl@atira.in) Website : [www.atira.in](http://www.atira.in)



Cert. No. TC-5097



## TEXTILE TESTING LABORATORY ISO/IEC 17025 : 2017 NABL ACCREDITED

(Linked to Ministry of Textile)

અહમદાબાદ વસ્ત્ર ઉદ્યોગ અનુસંધાન સંસ્થાન

પી. ઓ. આંબાવાડી વિસ્તાર, અહમદાબાદ-380 015. ભારત.

### TEST REPORT

Format No.: TT 10/01/00

|  |  |
|--|--|
| ULR NUMBER TC 5097 21 2 00005459F                                  |  |
| Test Report No: A/T/0944 2021-22                                   | Date: 29.09.2021   |
| Mill/Company/Customer:   | Nirvana Tex Mills  |
| Address & Contact Details:   | 290 Malliya, New Cloth Market<br>Sarangpur, Ahmedabad-380002<br>Email : <a href="mailto:nirvanatexmills@gmail.com">nirvanatexmills@gmail.com</a> |
| Sample forwarding Letter No. & Date:                               | Nil dated Nil  |
| Date of receipt of Sample:   | 27.09.2021   |
| Lab Sample Code No. :  | TT - 3316  |
| Number of Samples : 01   |  |
| Date of Performance of test(s): 28.09.2021 to 29.09.2021           |  |
| Samples Description : Sample Design No "Amrit Zure +SharpEN - Rust |  |

Discipline / Group : Chemical Testing / Textiles

| Sr. No. | Test Parameters  | Unit   | Test Method                         | Test Results                  |
|---------|--|--------|-------------------------------------|-------------------------------|
| 1       | Dimensional Stability<br>Warp<br>Weft  | %      | AATCC 135<br>@ 40° C<br>Single Wash | -3.04<br>-4.00                |
| 2       | Colour Fastness to Water<br>Change in colour<br>Staining on adjacent<br>Polyester/Cotton/Wool<br>Nylon/Acrylic/Acetate | Rating | ISO 105 E01                         | 4-5<br>4-5/4/4<br>4-5/4-5/4-5 |

Page 1 of 1

★★ ISO : 17025 Accredited Laboratories ★★

AUTHORISED SIGNATORY  
Textile Testing Laboratory  
ATIRA, Ahmedabad

Samples are not drawn by AITRA. Result relates to the samples tested. The report shall not be reproduced except in full, without written approval of the laboratory. The report is strictly confidential and for technical information of client only. Not for Advertisement, Promotion, Publicity or Litigation, Please write Test Report number and date for all future correspondence.

#### Grey Scale Rating

5. Excellent 4. Good  
3. Fair 2. Poor  
1. Very Poor

#### Pilling Rating

5. No Pilling 4. Slight Pilling  
3. Moderate Pilling 2. Severe Pilling  
1. Very Severe Pilling

Sample conditioned and tested at temp. of 27±2° (Instead of 20/21±2/1° C) and 65±2% RH wherever ISO / ASTM / AATCC test methods adopted

GOOD BUSINESS ARE MEMBERS OF ATIRA : ATIRA MEMBERSHIP IS GOOD BUSINESS