LEFTA the assembly was carried out in acidic medium

LEFTB using Pluronic P123 as the structure directing

LEFTC agent and TEOS as the silica source at 35 C

LEFTD followed by aging for twenty hours in a bottle

RIGHTA the calcined material gave a type IV isotherm

RIGHTB with a BET surface area of 820 m2/g and a

RIGHTC narrow pore size distribution centred at 7.8 nm

RIGHTD as measured on the adsorption branch by BJH