A Two Column Paper About Mesoporous Silica

LEFTA the assembly was carried out in acidic medium
LEFTB using Pluronic P123 as the structure directing
LEFTC agent and TEOS as the silica source at 35 C
LEFTD followed by aging for twenty hours in a bottle

RIGHTA the calcined material gave a type IV isotherm
RIGHTB with a BET surface area of 820 m2/g and a
RIGHTC narrow pore size distribution centred at 7.8 nm
RIGHTD as measured on the adsorption branch by BJH