



# OHRA HYDRO POLYMERS PVT. LTD.

ADVANCED MATERIAL SCIENCE DIVISION

TECHNICAL DATA SHEET (TDS)

## OHRA-BOND™ CAL

SPEC ID: OC-TBC-REV01 | CATEGORY: SOIL CONDITIONING BINDER | DISTRIBUTION: GLOBAL

### PRODUCT DESCRIPTION

OHRA-BOND™ CAL is a specialized hybrid binder formulated with **Micronized Agricultural Calcium Sulfate Dihydrate** and activated hydrocolloids. It is specifically engineered for **Heavy Clay** and **Hardpan** soils.

The Calcium ions in the matrix chemically flocculate (loosen) tight clay particles, improving water infiltration and preventing crusting, while the hydrocolloid network seals the surface against wind and water erosion. This is the ideal "Volume Solution" for construction pads and large-scale dust control.

### KEY ADVANTAGES

- Clay Flocculation:** Chemically softens hard clay soils to allow root penetration and water absorption.
- Cross-Linked Durability:** Calcium ions create cross-links with the polymer, enhancing water-resistance.
- High Density:** Heavier bulk density allows for longer casting distances from the hydroseeder cannon.
- Economical:** The most cost-effective solution for large-area flat work.

### TECHNICAL SPECIFICATIONS

| Property         | Typical Value*                           | Test Method |
|------------------|------------------------------------------|-------------|
| Physical State   | Fine Powder Mix                          | Visual      |
| Appearance       | Light Grey / Off-White                   | Visual      |
| Active Matrix    | Calcium Sulfate Dihydrate + Hydrocolloid | --          |
| Calcium (Ca)     | > 18%                                    | ICP-AES     |
| Swell Volume     | Moderate (20-25 ml/g)                    | USP <601>   |
| pH (1% Solution) | 6.5 - 7.5 (Neutral)                      | ASTM D1293  |

\*Natural Product Disclaimer: Values listed are typical.

### APPLICATION INSTRUCTIONS

Important: Maintain agitation. Due to the high density of Calcium Sulfate Dihydrate, stop-and-go agitation may cause settling.

| Condition / Slope   | Application Rate (lbs/acre) | Kg / Hectare |
|---------------------|-----------------------------|--------------|
| Dust Control (Flat) | 30 - 40 lbs                 | 33 - 45 kg   |
| Construction Pad    | 40 - 50 lbs                 | 45 - 56 kg   |

|                  |             |            |
|------------------|-------------|------------|
| Clay Slope (3:1) | 50 - 60 lbs | 56 - 67 kg |
|------------------|-------------|------------|

PACKAGING & STORAGE

**Packaging:** Standard 50 lb (22.7 kg) Moisture-Resistant Industrial Bags.

**Storage:** Store in a cool, dry place. Keep away from moisture.

**DISCLAIMER OF WARRANTY AND LIMITATION OF LIABILITY:**  
OHRA HYDRO POLYMERS PRIVATE LIMITED extends no warranties, express or implied, regarding accuracy. The product is sold "AS IS". User assumes all risk.