Product Name	**MightyFix Polyurethane Sealant PU41**	**Pack Format**	600 mL Sausage (Soft Film)
Product Type	Moisture-Curing, 1-Component PU Sealant	**Standards**	GB/T 14683 | JC/T 946
Application Area	Construction Joints & Automotive Sheet Metal	**Availability**	Black / White / Grey

01 UNCURED PROPERTIES (23 °C / RH 50%)

Property	Unit	Value / Result
Appearance	—	Black / White / Grey paste, no flow
Density	g/cm³	1.42 – 1.50
Sag (Vertical)	mm	0 (no sagging)
Extrusion Rate	mL/min	≥ 90
Surface Drying Time	min	25 – 40
Through-Cure Rate	mm / 24 h	3 – 5
Full Cure	days	7
Application Temperature	°C	+5 to +35
Cure Mechanism	—	Atmospheric moisture

02 CURED PHYSICAL PROPERTIES (7 days, 23 °C / RH 50%)

Property	Unit	Standard	Typical Value
Shore A Hardness	Shore A	GB/T 14683	55 – 65
Tensile Strength	MPa	GB/T 14683	1.8 – 2.5
Elongation at Break	%	GB/T 14683	≥ 450
Movement Capability	%	ISO 11600	±25 (Class 25LM)
Elastic Recovery	%	GB/T 14683	≥ 85
Long-Term Temperature Resistance	°C	—	−55 to +120
Short-Term Temperature Resistance	°C	—	Up to +150
Water Absorption (24 h)	%	GB/T 14683	< 0.3
Adhesion Failure Mode	%	—	≥ 90% cohesive (substrate)

03 CHEMICAL RESISTANCE & ENVIRONMENTAL COMPLIANCE

Category	Resistant / Compliant	Limitations / Notes
Chemical Resistance	Water, engine oil, weak acids, weak alkalis	Not resistant to prolonged UV; cover when exposed
VOC / Solvents	Low VOC | Benzene-free | Oxime-free	Complies with GB 18583
Export Compliance	Passes AS/NZS 4020 (potable water systems)	Suitable for international markets
Silicone Content	Silicon-free	Fully paintable; no paint adhesion issues
Overcoatability	Paintable after full cure	No anti-paint coating required

04 PACKAGING & STORAGE

Item	Details
Pack Sizes	300 mL rigid cartridge | 600 mL sausage (soft film)
Shelf Life	12 months from date of manufacture
Storage Conditions	Store in a cool, dry, shaded location. Keep away from direct sunlight and moisture.
Application Equipment	Standard sausage gun / bulk dispensing equipment for 600 mL sausage packs

05 DIRECTIONS FOR USE

Surface Preparation

- Clean all joint surfaces. Remove dust, grease, oil, loose particles, and old sealant.
- Ensure surfaces are dry before application. Do not apply to wet or frost-covered surfaces.
- Prime porous substrates (concrete, masonry) with a compatible PU primer where required.

Application

- Load 600 mL sausage into appropriate dispensing gun. Cut nozzle to required diameter at 45°.
- Apply evenly into joint in one continuous pass. Avoid air entrapment.
- Tool the sealant within the open time to ensure full contact and a neat finish.
- Apply only within the recommended temperature range of +5 °C to +35 °C.

Curing

- Curing is initiated by atmospheric moisture. Allow adequate ventilation in enclosed areas.
- Do not apply masking tape after surface skin has formed (typically 25 – 40 min).
- Full mechanical properties are reached after 7 days at 23 °C / 50% RH.

06 HEALTH, SAFETY & HANDLING

- Contains isocyanate pre-polymers. Avoid prolonged skin or eye contact. Use appropriate PPE (gloves, safety glasses).
- Ensure adequate ventilation during application and curing, especially in confined spaces.
- In case of skin contact, remove immediately with soap and water. Seek medical attention if irritation persists.
- Keep away from children. Do not ingest.
- Refer to the Safety Data Sheet (SDS) for complete hazard and first-aid information.

DISCLAIMER

The technical data presented in this document is based on laboratory testing under controlled conditions and is provided in good faith. Values are typical and not guaranteed minimums. Users are responsible for verifying suitability for their specific application and conditions. The manufacturer accepts no liability for misuse or application outside stated parameters. Specifications may be revised without notice.