WOODELLO NC COLOR FINISH

WOODELLO™
FACTORIES TO HOMES

Premium Nitrocellulose Wood Coating

PRODUCT OVERVIEW

Woodello NC Color Finish is a premium nitrocellulose-based coating designed to deliver a smooth, durable, and high-gloss finish on wooden and metal surfaces. Its fast-drying formula provides rich colour depth, excellent clarity, and easy application, making it ideal for furniture, handicraft items, and decorative surfaces.

Ideal for:

- Furniture
- Doors & Window Frames
- Cabinets & Wardrobes
- Interior Wooden Panels
- Decorative Wooden Surfaces





PRODUCT CODE 006

KEY FEATURES

Superior Durability
Long-lasting coating that protects furniture from everyday wear.

Excellent Gloss Retention
Maintains shine and beauty for years.


Easy Application
Can be applied by spray or brush.

Interior & Exterior Compatibility
Suitable for multiple wooden applications.

Smooth Premium Finish
Delivers a professional furniture-grade coating.

AVAILABLE PACKS

WOODELLO NC COLOR FINISH
500ml, 1L & 4L



500ml 1L 4L




COLOURS AVAILABLE

Clear
Available in a range of 5 attractive Woodello colour shades for interior and exterior applications, designed to enhance or customise the natural beauty of wood while providing a smooth decorative finish.

COVERAGE

Approximate coverage:
8–10 sq. meter / litre / coat
(on smooth sanded wooden surface using spray)



*Coverage may vary depending on surface condition and application method.

AVAILABLE FINISHES

- Excellent Gloss
- Smooth Finish


Smooth Finish


Excellent Gloss

COLOURS OPTIONS


Black Brown Golden Brown White PO Red

HOW TO APPLY

SURFACE PREPARATION



SANDING & INSULATING:
Sand the wooden surface along the grain using sandpaper no. 180, followed by 320 or 400 grit to achieve a smooth surface. Wipe the surface to remove loose dust particles.



DENT FILLING:
If the surface has dents or cracks, apply Woodello Wood Filler using a putty knife over the affected area and level the surface properly.

Registered Office: Marudhar Chemicals, G1-42, Boranada Industrial Park, Boranada, Jodhpur, Rajasthan – 342012, India. For feedback or product enquiries, please contact our Customer Care Manager at +91-291-2741060 or email support@marudharchemicals.com. You can also visit our website at www.woodello.in for more information.

Version No. WE01/03/2026. This datasheet supersedes all previous versions. © Marudhar Chemicals. All rights reserved. Terms and conditions apply.
Please refer to the product warranty document for detailed information.

WOODELLO™
FACTORIES TO HOMES

APPLICATION SYSTEM AND MIXING DETAILS

APPLICATION	CODE	WOODELLO THINNER	% DILUTION (BY VOLUME)	APPLICATION VISCOSITY (SEC)	RECOATING PERIOD (HRS.)
STEP 1 Woodello NC Color Finish - First Coat (Spray/Brush)	006	Woodello NC Thinner	Spray 80-100 Brush 40-50	Spray 18–22 sec Brush 30–40 sec	20–30 minutes
STEP 2 Sanding	Sand the surface with sand paper 320 or 400 and wipe clean				
STEP 3 Woodello NC Color Finish- Second Coat (Spray/Brush)	006	Woodello NC Thinner	Spray 80-100 Brush 40-50	Spray 18–22 sec Brush 30–40 sec	20–30 minutes
STEP 4 Sanding	Sand the surface with sand paper 320 or 400 and wipe clean (For best results, apply over Woodello NC Sanding Sealer as an undercoat.)				

Note: Ensure the wooden surface is properly sanded and free from dust, oil, grease, or other contaminants before application. For better surface preparation and smooth finishing, Woodello NC Sanding Sealer may be used as an undercoat before applying Woodello NC Color Finish. Stir the material thoroughly before use and dilute only with Woodello Multipurpose Thinner as recommended. Do not mix with other paint systems or hardeners. Apply thin and uniform coats, allowing proper drying between coats. The recoating time mentioned is based on 30°C temperature and 75% relative humidity and may vary depending on environmental conditions. Recommended spray pressure is 2.2–2.8 kg/cm², and viscosity is measured using a Ford Cup B4 at 30°C. Ensure containers are tightly closed after use to avoid contamination and solvent evaporation.

ADDITIONAL INFORMATION

POST APPLICATION CARE

If coating material spills on tiles or metal surfaces, clean immediately using Woodello NC Thinner and wipe with a clean cloth. During spraying or brushing, surrounding areas should be properly masked to prevent stains on adjacent surfaces.

PRODUCT SPECIFICATIONS

Drying Time:
- Surface Dry: Approx. 20–30 minutes
- Hard Dry: Approx. 1 hour

Gloss Level:
- Gloss Finish: Minimum 80% (at 60° Gloss Meter)

Flash Point:
- Above 30°C

Stability of Thinned Material:
- Use the prepared mixture within 8 hours.

Shelf Life:
- Up to 3 years from date of manufacture when stored in tightly closed containers away from heat and direct sunlight.

APPLICATION RECOMMENDATIONS

For best results, apply Woodello NC Color Finish at temperatures between 20°C and 40°C and relative humidity below 75%. Do not over-thin the material and always follow the recommended dilution ratio using Woodello NC Thinner. Stir well and strain before use.

SAFETY INFORMATION

Refer to the Material Safety Data Sheet (MSDS) for detailed handling instructions. Store the product in a cool, well-ventilated area away from heat, sparks, and open flames. Use protective equipment such as gloves, safety goggles, and masks during application. Avoid contact with eyes and skin; in case of contact, wash immediately with soap and plenty of water. In case of inhalation, move to fresh air and seek medical attention if discomfort persists.
This product contains no added Lead, Mercury, or Chromium compounds and is flammable. Dispose of leftover paint and containers responsibly through authorized waste management agencies.

Registered Office: Marudhar Chemicals, G1-42, Boranada Industrial Park, Boranada, Jodhpur, Rajasthan – 342012, India. For feedback or product enquiries, please contact our Customer Care Manager at +91-291-2741060 or email support@marudharchemicals.com. You can also visit our website at www.woodello.in for more information.

Version No. WE01/03/2026. This datasheet supersedes all previous versions. © Marudhar Chemicals. All rights reserved. Terms and conditions apply.
Please refer to the product warranty document for detailed information.