

# ADDITOL® VXW 6206

## TYPE

Water-emulsifiable, nonylphenolic ethoxylatefree combination drier

## FORM OF DELIVERY (f.o.d.)

Metal content

approx. 5.00 % Cobalt  
approx. 0.22 % Lithium  
approx. 7.50 % Zirconium

## PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	150 - 1000
---	---------	------------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	63 - 68
--	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour		violet
---------------------------------------	--	--------

Ash Content DIN EN ISO 6245 content approx.	[%]	16
---	-----	----

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm³]	1,09
--	---------	------

Flash Point (CCCFP) ASTM D 6450 flash point approx.	[°C]	66
---	------	----

## SPECIAL PROPERTIES

The leadfree and bariumfree combination drier Additol VXW 6206 produces in waterborne alkyd resin paints a good set-drying combined with an even through-drying.

Additol VXW 6206 contains a balanced metal combination which is for an optimum oxidative drying necessary.

## SUGGESTED USES

Additol VXW 6206 may be added as siccative to all waterborne oxidatively drying alkyd resin paints. Especially suitable for externally emulsified alkyd resin emulsions.

## PROCESSING

Additol VXW 6206 may be added undiluted to the resin in form of delivery. In crucial systems, tendency to speck formation, we recommend dispersing the combination drier with the pigments and fillers.

Recommended quantity to be added: 1.0 - 3.0 %, calculated on solid resin.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

When stored at temperatures below 20 °C Additol VXW 6206 tends to slight crystallization, which is reversible by heating for 24 hours to 40 °C.

## DISTINGUISHING FEATURES

In comparison to Additol VXW 4940, Additol VXW 6206 contains no barium siccative and it is nonylphenolic ethoxylatefree. It is more easily incorporated into externally emulsified waterborne alkyd resins.

4.0/17.07.2013 ( replaces all previous versions )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.