
D = 8 mm
D = 9 mm
D = 10 mm
Solid panel
XFOIL
(a) Horizontal
(b) Vertical
(c) Horizontal + Vertical
Pressure-drag coefficient, C_D
0.08
0.06
0.04
0.02
0.00
−4
0
4
8
12
16
Angle of attack, α [deg]