

## PRODUCT SPECIFICATIONS

### EasyGrid 3-150GC (Geocomposite Geogrid)

**EasyGrid 3-150GC** is a geo-composite consisting of a polypropylene extruded biaxial geogrid thermally bonded with a UV stabilized polypropylene needle punched nonwoven geotextile. It is manufactured at a facility that has achieved ISO 9001:2008 certification for its systematic approach to quality. The construction of the geocomposite makes it ideal for reinforcement, road construction, landfill applications and in many fields of civil engineering.

| PROPERTY                                       | TEST                    | UNIT              | VALUE           |              |
|------------------------------------------------|-------------------------|-------------------|-----------------|--------------|
| Mechanical                                     |                         |                   | MD              | CD           |
| Tensile Strength                               | ASTM D6637              | kN/m<br>(lb/ft)   | 32<br>(2193)    | 32<br>(2193) |
| Elongation at Maximum Load                     | ASTM D6637              | %                 | 10              | 10           |
| Tensile Strength @ 2% Strain                   | ASTM D6637              | kN/m<br>(lb/ft)   | 9<br>(617)      | 10<br>(685)  |
| Tensile Strength @ 5% Strain                   | ASTM D6637              | kN/m<br>(lb/ft)   | 22<br>(810)     | 24<br>(1340) |
| Rib Strength                                   | GRI GG1                 | kN/m<br>(lb/ft)   | 29<br>(1987)    | 29<br>(1987) |
| Junction Strength                              | GRI GG2                 | kN/m<br>(lb/ft)   | 27<br>(1850)    | 27<br>(1850) |
| Junction Efficiency                            | GRI GG2 &<br>ASTM D6637 | %                 | 90              |              |
| Flexural Rigidity                              | ASTM D1388              | mg-cm             | 4,000,000       |              |
| Type 150 Nonwoven                              |                         |                   |                 |              |
| Resistance to Static Puncture                  | ASTM D6241              | N                 | 2100            |              |
| Characteristic Opening Size (O <sub>90</sub> ) | EN ISO 12956            | µm                | 90              |              |
| Water Flow Rate                                | ASTM D4491              | sec <sup>-1</sup> | 2               |              |
| Physical                                       |                         |                   |                 |              |
| Grid Opening Size                              | Measured                | mm<br>(in)        | 40<br>(1.57)    | 40<br>(1.57) |
| Carbon Black                                   | ASTM D1603              | %                 | 2               |              |
| Packaging                                      |                         |                   |                 |              |
| Roll Width                                     | Measured                | m<br>(ft)         | 3.95<br>(12.96) |              |
| Roll Length                                    | Measured                | m<br>(ft)         | 50<br>(164)     |              |

*Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.*

