

PRODUCT SPECIFICATIONS

EasyGrid 4-150GC (Geocomposite Geogrid)

EasyGrid 4-150GC is a geo-composite consisting of a polypropylene extruded biaxial geogrid thermally bonded with a UV stabilized polypropylene needle punched nonwoven geotextile. It is manufactured at a facility that has achieved ISO 9001:2008 certification for its systematic approach to quality. The construction of the geocomposite makes it ideal for reinforcement, road construction, landfill applications and in many fields of civil engineering.

PROPERTY	TEST	UNIT	VALUE	
Mechanical			MD	CD
Tensile Strength	ASTM D6637	kN/m (lb/ft)	40 (2741)	40 (2741)
Elongation at Maximum Load	ASTM D6637	%	12	12
Tensile Strength @ 2% Strain	ASTM D6637	kN/m (lb/ft)	15 (1028)	15 (1028)
Tensile Strength @ 5% Strain	ASTM D6637	kN/m (lb/ft)	26 (1782)	30 (2056)
Rib Strength	GRI GG1	kN/m (lb/ft)	41 (2809)	41 (2809)
Junction Strength	GRI GG2	kN/m (lb/ft)	38 (2604)	38 (2604)
Junction Efficiency	GRI GG2 & ASTM D6637	%	90	
Flexural Rigidity	ASTM D1388	mg-cm	> 5,000,000	
Type 150 Nonwoven				
Resistance to Static Puncture	ASTM D6241	N	2100	
Characteristic Opening Size (O ₉₀)	EN ISO 12956	μm	90	
Water Flow Rate	ASTM D4491	sec ⁻¹	2	
Physical				
Grid Opening Size	Measured	mm (in)	40 (1.57)	40 (1.57)
Carbon Black	ASTM D1603	%	2	
Packaging				
Roll Width	Measured	m (ft)	3.95 (12.96)	
Roll Length	Measured	m (ft)	45 (148)	

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.

