DATA SHEET

BLANKET FOR EROSION CONTROL - STRAW AND COIR FIBERS

PRODUCT DESCRIPTION: Blanket composed of a mixture of straw and coir fibers of which 75 % of fibers are 100 mm (4 in) long or more. The top is covered with black oxo-biodegrader polypropylene netting, and the bottom is covered with green oxo-biodegrader polypropylene netting and both netting contain UV additives.

FUNCTION: Control

RAW MATERIAL: Straw (70 %) fibers, coir fibers (30 %) and polypropylene mesh

TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Thickness	ASTM D6525	6.78 mm	0.267 in
	Mass per unit area	ASTM D6475	228 g/m²	0.05 lb/ft²
	Resiliency	ASTM D6524	74.0 %	
	Light penetration	ASTM D6567	15.0 %	
MECHANICAL	Tensile strength MD	ASTM D6818	2.97 kN/m	203.5 lb/ft
	Tensile strength TD	ASTM D6818	2.12 kN/m	145.0 lb/ft
	Elongation at break MD	ASTM D6818	27.54 %	
	Elongation at break TD	ASTM D6818	36.52 %	
PERFORMANCE AND DURABILITY	Functional longevity(4)	-	≤ 24 months	
OTHER	Swelling	ECTC procedure	55.0 %	
	Water absorbency	ASTM D1117/ECTC	415.0 %	
	Laboratory testing of rain splash	ASTM D7101	SLR = 12.51 @ 2 in/hr(2.3)	
			SLR = 12.72 @ 4 in/hr(2.3)	
			SLR = 12.98 @ 6 in/hr(2.3)	
	Shear test	ASTM D7207	2.11 lb/ft² @ 0.5 in of soil loss	
	Germination improvement	ASTM D7322	465.0 %	
DIMENSIONS AND WEIGHT	Width	-	2.44 m	8.0 ft
	Length	-	34.29 m	112.5 ft
	Surface	-	83.67 m²	900.0 ft²
	Weight (± 10 %)	-	22.7 kg	50.0 lb
	Mesh openings	Polypropylene (black HV) on top	19.1 mm x 19.1 mm	0.75 in x 0.75 in
		Polypropylene (green) underneath	12.7 mm x 12.7 mm	0.50 in x 0.50 in

Note 1: Weight is based on the dry fibre. During its manufacture, the reference humidity levels are 20 % for coir fibers, and 15 % for straw.
Note 2: SLR is the soil leach ratio, as defined by NTPEP/AASHTO.
Note 3: The laboratory tests indexes should not be used for design purposes.
Note 4: Functional longevity varies from region to region because of differences in climatic conditions.

The enclosed information is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5 % from standard sizes.

Soleno Textile Inc. offers no guarantee regarding the use, installation or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractual warranty.

Mastering Storm Water

DATA SHEET

BLANKET FOR EROSION CONTROL - STRAW AND COIR FIBERS (CONT.)

Straw and coir mats are designed to channel a flow rate up to 2.6 m/s (8.5 ft/s) and 96 N/m^2 (2.0 lbs/ft^2) of shear stress limit.

Straw and coir mats have a rate of soil loss of 0.15 and are generally appropriate for slopes up 1.5H:1V.

APPLICATIONS: Retaining walls and embankments
Grow vegetation areas