

ACECompo™ GS is a geocomposite made of fiberglass yarns and a layer of needle-punched polyester nonwoven geotextile, and is usually used in the reinforcement of road base and pavement layers. The fiberglass yarns have high tensile strength (up to 100kN/min biaxial directions) and modulus to offer reinforced force, and limit the deformation of structures or soils implanted with ACECompo™ GS geocomposites. The nonwoven geotextiles provide functions of filtration, separation and drainage. When used in asphalt pavement reinforcement, it can absorb bituminous materials to enhance the bonding to asphalt layers. The multifunction of ACECompo™ GS geocomposites make their applications extensive including asphalt or concrete pavement reinforcement, base reinforcement and soil stabilization.

Product Properties

Test Method	Unit	GS 50-II	GS 100-II
-------------	------	----------	-----------

Mechanical Properties

Material			Glassfiber Yarns with Polyester Needle Punched Nonwoven Geotextile	
Mesh Size, -10%	Measured	mm	25.4 × 25.4	25.4 × 25.4
Tensile Strength-MD, -10%	ASTM D4595	kN/m	50	100
Tensile Strength-CD, -10%	ASTM D4595	kN/m	50	100
Tensile Elongation-MD	ASTM D4595	%	4	4
Tensile Elongation-CD	ASTM D4595	%	4	4

Dimensional Characteristics

Length		m	50	50
Width		m	3.9	3.9

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
 We can customize the product to fulfill different project requirement. If you require more detail information,
 please feel free to contact us directly at sales@geoace.com.
 We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
 E-mail: sales@geoace.com <http://www.geoace.com>