

ACECompo™ PETB are geocomposites comprised of unilateral or bilateral polyester yarns incorporated into a polypropylene or polyester needle-punched nonwoven geotextile. The polyester yarns have high tensile strengths, which are up to 200 kN/m in uniaxial direction and 100kN/m in biaxial directions, for performing the function of reinforcement, and the nonwoven geotextiles provide the excellent capability of separation, filtration and drainage. For high-loaded roadways or railways, ACECompo™ PETB offer an effective reinforcement to extend their service life or reduce the course material requirement with cost efficiency.

Product Properties

Test Method	Unit	PETB 50-I	PETB 100-I
-------------	------	-----------	------------

Mechanical Properties

Material			Polyester Yarns + Polyester Needle Punched Nonwoven Geotextile	
Tensile Strength-MD, -10%	ASTM D4595	kN/m	50	100
Tensile Strength-CD, -10%	ASTM D4595	kN/m	14	14
Tensile Elongation-MD	ASTM D4595	%	16	16

Hydraulic Property

Water Permeability Normal to the Plane, -30%	ASTM D4491	L/m²s	60	60
--	------------	-------	----	----

Dimensional Characteristics

Length		m	100	100
Width		m	5.3	5.3

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract.
We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>