



ACEDrain™ G geomesh is made of high impact polymer with 4mm to 6mm thick range. It can maintain a constant thickness under high load pressure and provide excellent conductivity. The geonets are generally laminated with a nonwoven geotextile on one or both surfaces to prevent soil from entering the water flow paths. The nonwoven geotextile is available in mass per unit area range of 120, 150, 200 g/m². Different combinations of drainage composite materials can be used in civil structures such as embankment, landfill and roadway.

Product Properties

	Test Method	Unit	G04-N12	G04-N15	G04-N20
Drainage Geocomposite					
Component type			Nonwoven Geotextile + Geonet		
Tensile Strength-MD/CD, -10%	ISO 10319	kN/m	10/8	11/8	13/10
Tensile Elongation-MD/CD	ISO 10319	%	50/50		
Flow Capacity in The Plane-MD (i=1.0, σ=200kPa), -30%	ISO 12958	L/m.s	0.76	0.68	0.61
Thickness at 2kPa, -1mm	ISO 9863-1	mm	4.5		
Mass per Unit Area, -10%	ISO 9864	g/cm²	580	600	650
Geonet Drainage					
Material			High-density Polyethylene		
Carbon Black	ASTM D4218	%	2~3		
Density	ASTM D1505	g/cm³	> 0.94		
Thickness at 2kPa, -1mm	ISO 9863-1	mm	4.2		
Geotextile Filtration					
Material			Polypropylene		
Mass per Unit Area, -10%	ISO 9864	g/cm²	120	150	200
CBR, -10%	ISO 12236	N	1200	1600	2200
AOS, +30%	ISO 12956	mm	0.17	0.15	0.1
Water Flow Rate, -30%	ISO 11058	L/m²s	80	55	25
Dimensional Characteristics					
Length		m	50	50	50
Width		m	3.8	3.8	3.8

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>