



ACEGrid® GDE are integrally formed uniaxial geogrids made of high density polyethylene (HDPE) through extrusion, punching and drawing. ACEGrid® GDE geogrids can carry high tensile loads applied in one direction with superior stiffness and junction strength for reinforcement applications including reinforced slopes, retaining walls and embankments.

Product Properties

	Test Method	Unit	GDE 45	GDE 50	GDE 60	GDE 65	GDE 80	GDE 90	GDE 110	GDE 120	GDE 130	GDE 145	GDE 150	GDE 160	GDE 170	GDE 200
--	-------------	------	--------	--------	--------	--------	--------	--------	---------	---------	---------	---------	---------	---------	---------	---------

Mechanical Index Properties

Tensile Strength -MD, -5%	ASTM D6637	kN/m	45	50	60	65	80	90	110	120	130	145	150	160	170	200
Tensile Elongation-MD	ASTM D6637	%	14	14	14	14	14	14	14	14	14	14	14	14	14	14
Tensile Strength at 2% Strain-MD, -5%	ASTM D6637	kN/m	9	10	13	15	18	21	27	30	32	36	39	42	47	53
Tensile Strength at 5% Strain-MD, -5%	ASTM D6637	kN/m	20	21	25	27	36	41	52	59	67	75	79	83	92	104

Dimensional Characteristics

Length		m	100	100	100	100	100	100	50	50	50	50	50	50	50	50
Width		m	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>