



ACEGrid® GDP are integrally formed biaxial geogrids made of polypropylene (PP) through extrusion, punching and drawing. ACEGrid® GDP geogrids can carry high tensile loads applied in both longitudinal and transverse directions with superior stiffness and junction strength for reinforcement applications, including pave or unpaved road construction, railway improvement and soft soil stabilization.

Product Properties

	Test Method	Unit	GDP 15-II	GDP 20-II	GDP 30-II	GDP 40-II
Mechanical Index Properties						
Tensile Strength, -5%	ASTM D6637	kN/m	15	20	30	40
Tensile Elongation	ASTM D6637	%	14	14	14	14
Tensile Strength at 2% Strain-MD, -5%	ASTM D6637	kN/m	5	7	10.5	14
Tensile Strength at 5% Strain-MD, -5%	ASTM D6637	kN/m	7	14	21	28
Dimensional Characteristics						
Length		m	50	50	50	50
Width		m	3.95	3.95	3.95	3.95

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
 We can customize the product to fulfill different project requirement. If you require more detail information,
 please feel free to contact us directly at sales@geoace.com.
 We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
 E-mail: sales@geoace.com <http://www.geoace.com>