



ACEMembrane™ are high-density polyethylene (HDPE) geomembranes with smooth or textured surfaces in either side for blocking or containing liquids, solids or waste materials. ACEMembrane™ geomembranes offer sufficient tensile strength and high resistance to puncture, tear, cracking, UV and chemicals with relatively small thicknesses. As a most common field fabricated geomembrane material, ACEMembrane™ have very wide applications, including landfill liners and covers, canal and reservoir liners, containment of coal ash and heap leach mining, etc.

Product Properties

	Test Method	Unit	HDT 75-I	HDT 100-I	HDT 150-I	HDT 200-I	HDT 250-I
--	-------------	------	----------	-----------	-----------	-----------	-----------

Mechanical Index Properties

Material			HDPE One Side Textured Geomembranes				
Nominal Thickness, -10%	ASTM D5994	mm	0.75	1.00	1.50	2.00	2.50
-Lowest individual for 8 out of 10 values	ASTM D5994	mm	0.68	0.90	1.35	1.80	2.25
-Lowest thickness for any of the 10 values	ASTM D5994	mm	0.64	0.85	1.28	1.70	2.13
Asperity Height	ASTM D7466	mm	0.40	0.40	0.40	0.40	0.40
Density	ASTM D792	g/cm ³	0.94	0.94	0.94	0.94	0.94
Tear Resistance, -10%	ASTM D1004	N	93	125	187	249	311
Puncture Resistance, -10%	ASTM D4833	N	200	267	400	534	667
Carbon Black Content	ASTM D1603	%	2~3	2~3	2~3	2~3	2~3
Carbon Black Dispersion	ASTM D5596	-	Note(1)	Note(1)	Note(1)	Note(1)	Note(1)

Tensile Properties (each direction)

Strength at Yield, width, -10%	ASTM D6693	kN/m	11	15	22	29	37
Strength at Break, width, -10%	Type IV	kN/m	8	10	16	21	26
Elongation at Yield (G.L 33mm)	Specimen	%	12	12	12	12	12
Elongation at Break (G.L 51mm)	@50 mm/min	%	100	100	100	100	100

Dimensional Characteristics

Width		m	8	8	8	8	7
Length		m	225	170	128	98	76

Note: (1) Carbon black dispersion for 10 different views : all 10 in Categories 1 or 2.

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>