



ACETex[®] ES is a woven geotextile made of high tenacity polypropylene (PP) yarns. This product has enhanced level of permeability with moderate opening size and high resistance to ultraviolet, chemical, and oxidation. It can be widely for reinforcement, separation, containment, and filtration long-termly.

Product Properties

Mechanical Index Properties	Unit	ES510	ES710	ES420	ES520	ES720	ES530	ES730	Test Method
Nominal Tensile Strength - MD	kN/m	55	70	--	--	--	65	85	ASTM D4595
Nominal Tensile Strength - CD	kN/m	50	70	--	--	--	45	85	ASTM D4595
Elongation at Break - MD	%	--	--	--	--	--	12	12	ASTM D4595
Elongation at Break - CD	%	--	--	--	--	--	10	10	ASTM D4595
Tensile strength at 2% strain - MD	kN/m	8	14	10	9	7	14	18	ASTM D4595
Tensile strength at 2% strain - CD	kN/m	8	22	10	15	27	16	32	ASTM D4595
Tensile strength at 5% strain - MD	kN/m	22	35	25	27	20	--	--	ASTM D4595
Tensile strength at 5% strain - CD	kN/m	23	45	25	33	65	--	--	ASTM D4595
Static Puncture Resistance (CBR)	N	5000	8000	7000	8000	10000	6000	9000	ASTM D6241

Mechanical Performance Properties

UV Resistance (500 hr)	%	90	90	90	90	90	90	90	ASTM D4355
------------------------	---	----	----	----	----	----	----	----	------------

Hydraulic Properties

Permittivity (50mm head)	1/sec	0.6	0.5	0.9	1	1	0.67	0.67	ASTM D4491
Flow Rate (50mm head)	l/min/m ²	1800	1500	2700	3000	3000	2000	2000	ASTM D4491
Apparent Opening Size(O ₉₅)	mm	0.425	0.6	0.425	0.425	0.425	0.3	0.3	ASTM D4751

Packing Properties

Width	m	4.5	4.5	4.5	4.5	4.5	4.5	4.5	
-------	---	-----	-----	-----	-----	-----	-----	-----	--

Notes:

1. The maximum width of ACETex[®] can reach 5.2m and width shown on the data sheet is the most effective.

2. The values given are indicative and correspond to an MARV results obtained in our QC laboratory. The right is reserved to make changes without notice.

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>