



ACETex® NW BNW series nonwoven geotextile is made of Polypropylene fiber, needle punched and with thermally bonded surface. They are offered with the high permeability, excellent drainage capacity, and controlled filtration properties.

Product Properties

	Test Method	Unit	BNW 6	BNW 8	BNW 13	BNW 16	BNW 21	BNW 25	BNW 30	BNW 34	BNW 40	BNW 46	BNW 62	BNW 75
--	-------------	------	-------	-------	--------	--------	--------	--------	--------	--------	--------	--------	--------	--------

Mechanical Index Properties

Tensile Strength-MD, -15%	ISO 10319	kN/m	5.5	7	11.5	14.5	19	22.5	27	30.5	36	41.5	56	67.5
Tensile Strength-CD, -15%	ISO 10319	kN/m	5.5	7	11.5	14.5	19	22.5	27	30.5	36	41.5	56	67.5
Tensile Elongation-MD, +20(value)	ISO 10319	%	50	55	60	60	60	60	65	65	65	65	65	65
Tensile Elongation-CD, +20(value)	ISO 10319	%	50	55	60	60	60	60	65	65	65	65	65	65
Puncture Strength, -10%	ISO 12236	N	760	1100	2000	2400	3150	3600	4150	4950	5850	7200	11000	13500

Hydraulic Property

AOS, +30%	ISO 12956	mm	0.15	0.14	0.11	0.095	0.075	0.075	0.075	0.075	0.075	0.075	0.075	0.075
Water Flow Rate, -30%	ISO 11058	l/m²/s	95	90	80	70	50	45	35	30	25	20	15	10

Dimensional Characteristics

Nominal Mass, -15%	ISO 9863	g/m²	80	100	160	200	260	300	360	450	500	600	800	1000
Thickness, -15%	ISO 9684	mm	0.8	0.9	1.3	1.4	1.6	1.8	2.0	2.5	2.7	3.3	4.5	5.9
Length		m	100	100	100	100	100	50	50	50	50	50	50	30
Width		m	5.9	5.9	5.9	5.9	5.9	5.9	5.9	5.9	5.9	5.9	5.9	5.9

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>