



ACETex® NW TPN series nonwoven geotextile is made of polyester continuous filaments, needle punched and with thermally bonded surface. They are offered with the high permeability, excellent drainage capacity, and controlled filtration properties.

Product Properties

	Test Method	Unit	TPN 120	TPN 150	TPN 200	TPN 250	TPN 300	TPN 350	TPN 400	TPN 450	TPN 500	TPN 600
--	-------------	------	---------	---------	---------	---------	---------	---------	---------	---------	---------	---------

Mechanical Index Properties

Tensile Strength-MD, -10%	ASTM D4595	kN/m	7.5	9.5	12	15	17	21.5	24.5	27.5	34	38
Tensile Strength-CD, -10%	ASTM D4595	kN/m	6.5	8.5	10	13	15	19	22.5	25.5	31	35
Tensile Elongation-MD, +10(value)	ASTM D4632	%	65	65	65	65	65	60	60	60	60	60
Tensile Elongation-CD, +10(value)	ASTM D4533	%	65	65	65	65	65	60	60	60	60	60
Puncture Strength, -10%	ASTM D6241	N	1250	1700	2150	2550	3050	3400	4150	4550	5500	6500

Hydraulic Property

AOS, +30%	ASTM D4751	mm	0.35	0.35	0.33	0.30	0.28	0.25	0.23	0.20	0.18	0.15
Water Flow Rate, -30%	ASTM D4491	l/m ² /s	75	70	65	60	55	55	35	30	25	25

Dimensional Characteristics

Nominal Mass, -10%	ASTM D5261	g/m ²	120	150	200	250	300	350	400	450	500	600
Thickness, -10%	ASTM D5199	mm	1.0	1.3	1.5	2.0	2.3	2.6	2.8	3.1	3.3	3.7
Length		m	250	200	150	120	100	85	75	65	60	50
Width		m	6	6	6	6	6	6	6	6	6	6

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>