



ACETex® SL are woven geotextiles fabricated from high tenacity and UV stabilized polypropylene yarns with stable structures, which offer high tensile strength, high durability and excellent resistances to puncture, pullout, deformation and installation damages.

Product Properties

	Test Method	Unit	SL 130	SL 190
Mechanical Index Properties				
Grab Tensile Strength-MD, -10%	ASTM D4632	N	890	1400
Grab Tensile Strength-CD, -10%	ASTM D4632	N	890	1400
Tearing Strength-MD, -10%	ASTM D4533	N	300	480
Tearing Strength-CD, -10%	ASTM D4533	N	300	480
CBR, -10%	ASTM D6241	N	2800	4000
Hydraulic Property				
AOS, +30%	ASTM D4751	mm	0.425	0.425
Permittivity, -30%	ASTM D4491	1/sec	0.05	0.05
Durability Property				
UV Resistance, -10%	ASTM D4355	%	90	90
Dimensional Characteristics				
Length		m	130	110
Width		m	3.81	3.81

Disclaimer: This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.

Thank you for your interests in our products,
We can customize the product to fulfill different project requirement. If you require more detail information,
please feel free to contact us directly at sales@geoace.com.
We'll be pleased to provide our best assistance.

Accurate, Collaborative, Efficient

TEL: 886-4-26595926 FAX: 886-4-26595935
E-mail: sales@geoace.com <http://www.geoace.com>