

# Technical Data Sheet

## Envirotex SymbioPark



|                      |                                                                            |
|----------------------|----------------------------------------------------------------------------|
| <b>Product</b>       | Decontamination geocomposite                                               |
| <b>Composition</b>   | Polypropylene, activated carbon, biostimulant nutrients, and fungal strain |
| <b>Main Function</b> | Filtration and decontamination of contaminated soils                       |

Envirotex SymbioPark is an innovative, preventive, and environmentally friendly solution designed to filter and decontaminate runoff and infiltration water in order to protect groundwater and preserve the environment. It is composed of two layers of anti-contaminant geotextiles enclosing activated carbon, biostimulant nutrients, and fungal strains. Envirotex SymbioPark is installed in the soil, between two layers of materials, in the same manner as a conventional separation/filtration geotextile.

| Property                    | Test Method | Upper Geotextile    | Lower Geotextile    |
|-----------------------------|-------------|---------------------|---------------------|
| Physical                    |             |                     |                     |
| Weight                      | ASTM D5261  | 200 g/m²            | 300 g/m²            |
| Thickness                   | ASTM D5199  | 2.2 mm              | 2.8 mm              |
| Mechanical                  |             |                     |                     |
| Tensile strength            | ASTM D4632  | 800 N               | 1 300 N             |
| Wide width tensile strength | ASTM D4595  | 12.5 kN/m           | 21 kN/m             |
| Elongation at break         | ASTM D4595  | 70%                 |                     |
| Tear resistance             | ASTM D4533  | 240 N               | 380 N               |
| CBR puncture                | ASTM D6241  | 2 000 N             | 3 300 N             |
| UV resistance               | ASTM D4355  | 50%                 |                     |
| Hydraulic                   |             |                     |                     |
| Permittivity                | ASTM D4491  | 1.8 s <sup>-1</sup> | 1.1 s <sup>-1</sup> |
| AOS <sup>1</sup>            | ASTM D4751  | 110 µm              | 90 µm               |

| Property                                                               | Test Method | Envirotex SymbioPark |
|------------------------------------------------------------------------|-------------|----------------------|
| <b>Physical</b>                                                        |             |                      |
| Weight of activated carbon, biostimulant nutrients, and fungal strains | -           | 80 g/m <sup>2</sup>  |
| Total weight of the geocomposite                                       | -           | 580 g/m <sup>2</sup> |
| <b>Dimensions</b>                                                      |             |                      |
| Width × Length                                                         | -           | 4m x 50m             |

The information originates from the manufacturer and has been transcribed by Texel. Properties are based on Minimum Average Roll Values (MARV) unless otherwise specified. The listed values are those obtained at the time of manufacturing. Handling and storage conditions may alter certain properties.

<sup>1</sup> Maximum Value

**Revision : 2026-04-28**

Texel reserves the right to modify the present properties based on the evolution of knowledge and techniques. The user is invited to verify whether this document represents the most recent update. Texel offers no warranty and assumes no responsibility for the use, installation, or suitability of the product. Texel must be informed of any defect or non conformity of the product prior to installation. Its liability is limited to the replacement of the non conforming or defective product.

**ALKEGEN**