



AMOCO FABRICS AND FIBERS COMPANY

KUBRICKY CONSTRUCTION CORP.
REVIEWED FOR SUBMISSION

STYLE 4553

Amoco Style 4553 is a polypropylene nonwoven needlepunched fabric. This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today. We wish to advise that Amoco Style 4553 meets the following minimum average roll values:

Property	Test Method	Minimum Average Roll Value (English)	Minimum Average Roll Value (Metric)
Grab Tensile	ASTM-D-4632	203 lbs	0.900 kN
Grab Elongation	ASTM-D-4632	50 %	50 %
Mullen Burst	ASTM-D-3786	400 psi	2750 kPa
Puncture	ASTM-D-4833	130 lb	0.575 kN
Trapezoidal Tear	ASTM-D-4533	80 lb	0.355 kN
UV Resistance	ASTM-D-4355	70 % at 500 hrs	70 % at 500 hrs
AOS	ASTM-D-4751	100 sieve	0.15 mm
Permittivity	ASTM-D-4491	1.5 sec ⁻¹	1.5 sec ⁻¹
Flow Rate	ASTM-D-4491	110 gal/min/R ²	4470 L/min/m ²

Amoco Fabrics and Fibers Company manufactures the nonwoven fabric indicated above. The values listed are a result of testing conducted in on-site laboratories. A letter certifying the minimum average roll values will be issued from the manufacturing plant by the Quality Control Manager at the time shipment is made.

DATE ISSUED: 01/01/98

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.