



AMOCO FABRICS AND FIBERS COMPANY
900 Circle 75 Parkway, Suite 300
Atlanta, GA 30339
PH: (770) 984-4444
FX: (770) 956-2430

KUBRICKY CONSTRUCTION CORP.
REVIEWED FOR SUBMISSION

STYLE 2002

Amoco Style 2002 is a polypropylene woven fabric. This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable.

Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today. We wish to advise that **Amoco Style 2002** meets the following minimum average roll values:

Property	Test Method	Minimum Average Roll Value (English)	Minimum Average Roll Value (Metric)
Grab Tensile	ASTM-D-4632	200 lb	0.890 kN
Grab Elongation	ASTM-D-4632	15 %	15 %
Mullen Burst	ASTM-D-3786	400 psi	2750 kPa
Puncture	ASTM-D-4833	90 lb	0.400 kN
Trapezoidal Tear	ASTM-D-4533	75 lb	0.330 kN
UV Resistance	ASTM-D-4355	70 % at 500 hr	70 % at 500 hr
AOS	ASTM-D-4751	50 sieve	0.300 mm
Permittivity	ASTM-D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Flow Rate	ASTM-D-4491	4 gal/min/ft ²	160 L/min/m ²

Amoco Fabrics and Fibers Company manufactures the woven fabric indicated above. The values listed are a result of testing conducted in on-site laboratories. A letter certifying the minimum average roll values will be issued from the manufacturing plant by the Quality Control Manager at the time shipment is made.

DATE ISSUED: 01/01/98