

ProPex® Nonwoven Geotextiles

Geotextiles and Geomembranes																		
PROPERTIES ¹	TEST METHOD	UNITS	4535	4545	4546	4547	4550	4551	4552	4553	4506	4508	4510		4512		4516	
PHYSICAL																		
Unit Weight	ASTM D 5261	oz/yd ²	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	6	8	10		12		16	
Grab Tensile Strength	ASTM D 4632	lb	80	90	100	120	135	160	180	203	160	203	250		300		390	
Grab Tensile Elongation	ASTM D 4632	%	50	50	50	50	50	50	50	50	50	50	50		50		50	
Mullen Burst	ASTM D 3786	psi	150	185	210	230	270	310	330	380	310	380	520		600		750	
Puncture	ASTM D 4833	lb	45	55	65	70	80	90	105	120	90	120	155		190		240	
Trapezoid Tear	ASTM D 4533	lb	35	40	45	50	56	65	75	80	65	80	100		115		150	
UV Resistance ²	ASTM D 4355	% @__hr	70@500	70@500	70@500	70@500	70@500	70@500	70@500	70@500	70@500	70@500	70@500		70@500		70@500	
HYDRAULIC																		
Apparent Opening Size (AOS) ⁴	ASTM D 4751	US Sieve	70	70	70	70	70	70	70	100	70	100	100		100		100	
Permittivity	ASTM D 4491	sec ⁻¹	2.2	2.1	2.0	1.8	1.7	1.5	1.5	1.5	1.5	1.5	1.2		0.9		0.7	
Permeability	ASTM D 4491	cm/sec	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	0.30	0.30	0.20		0.20		0.20	
Flow Rate	ASTM D 4491	gal/min/ft ²	160	155	145	130	120	110	110	110	110	110	85		65		50	
PACKAGING																		
Roll Width		ft	15	15	15	15	15	15	15	15	15	15	15		15		15	
Roll Length		ft	360	360	360	360	360	300	300	300	900	600	180	600	180	450	180	300
Gross Weight ³		lb	160	180	195	210	225	225	260	290	680	590	230	700	275	630	370	560
Area		yd ²	600	600	600	600	600	500	500	500	1500	1000	300	1000	300	750	300	500
SUGGESTED APPLICATIONS																		
Separation			X	X	X	X	X	X	X	X	X	X	X		X		X	
Stabilization						X	X	X	X	X			X		X		X	
Erosion Control/Drainage			X	X	X	X	X	X	X	X			X		X		X	
Railroad Stabilization													X		X		X	
Environmental/Waste											X	X	X		X		X	
MINIMUM AVERAGE ROLL VALUES																		

N/A - Not Applicable

- Physical and hydraulic properties reported as minimum average roll values (MARV)
- Percent grab tensile strength retained per hours of UV exposure following conditioning in accordance with ASTM D 43.
- Gross weights are approximate
- AOS reported as maximum average value

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.

DATE ISSUED: 01/01/04
Replaces all prior versions

