



Beltech 4 x 4

Product Data Sheet June 2014

A woven geotextile fabric, produced from polypropylene slit-film tapes, which will meet or exceed the following MARV's.

Property	Test Method	English Units			SI Units		
		MARV			MARV		
		MD	CD		MD	CD	
Wide Width Tensile Ultimate	ASTM D-4595	400	400	lbs/in	70	70	kN/m
Wide Width Elongation	ASTM D-4595	19	13	%	19	13	%
Trapezoid Tear	ASTM D-4533	260	205	lbs	1157	912	N
Puncture	ASTM D-4833	260		lbs	1157		N
CBR Puncture	ASTM D-6241	2250		lbs	10		kN
Permittivity	ASTM D-4491	0.22		sec ¹	0.22		sec ¹
A.O.S.	ASTM D-4751	45		U.S. Sieve	0.355		mm
UV Resistance (1200 hrs)	ASTM D-4355	70		%	70		%
Water Flow Rate	ASTM D-4491	16.5		gpm/ft ²	672		l/min/m ²



Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user.