



## ■ FX<sup>®</sup>-100PET

Carthage Mills' FX-100PET is a uniaxial high-performance/high-strength woven polyester geotextile that was developed for the most demanding reinforcement applications. FX-100PET is composed of high tenacity, high molecular weight multifilament polyester (PET) yarns that are woven into a stable network placed under tension. FX-100PET is part of the Carthage [FX<sup>®</sup> High-Strength Series](#) of woven geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Values reported are from a lab accredited by a2La (The American Association for Laboratory Accreditation) and Geosynthetic Association Institute – Laboratory Accreditation Program (GAI-LAP).

| PROPERTY                                                      | TEST METHOD                     | DATA<br>(Machine Direction)                        |                                                       |
|---------------------------------------------------------------|---------------------------------|----------------------------------------------------|-------------------------------------------------------|
|                                                               |                                 | METRIC                                             | ENGLISH                                               |
| <input type="checkbox"/> <b>Mechanical/Performance/Design</b> | ASTM D 4595                     |                                                    |                                                       |
| Wide Width Tensile (at ultimate)                              |                                 | 100.0 kN/m                                         | 570.8 lbs/in<br>6,850 lbs/ft                          |
| Tensile Strength (at 5% strain)                               |                                 | 35.0 kN/m                                          | 200 lbs/in<br>2,400 lbs/ft                            |
| Factory Sewn Seam - CD                                        | ASTM D 4884                     | 24.8 kN/m                                          | 141.6 lbs/in<br>1,700 lbs/ft                          |
| <input type="checkbox"/> <b>Physical</b>                      | Measured<br>(Typical/Estimated) |                                                    |                                                       |
| Standard Roll Dimensions <sup>(1)</sup>                       |                                 | 5.0 m x 100.0 m<br>500 m <sup>2</sup><br>151.95 kg | 16.41 ft x 328.1 ft<br>598 yd <sup>2</sup><br>335 lbs |
| Packaging                                                     |                                 | 5.0 m x 300.0 m<br>1500 m <sup>2</sup><br>-        | 16.41 ft x 984.3 ft<br>1794 yd <sup>2</sup><br>-      |
| Weight                                                        |                                 |                                                    |                                                       |

<sup>(1)</sup> Custom lengths and factory fabricated wide width panels are available by Special Order.

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-18 and are subject to change without notice.

★ Proudly Made in the U.S.A.! ★

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.