



■ FX[®]-300MF

Carthage Mills' FX-300MF is a woven High-Performance geotextile produced from high-tenacity polypropylene yarns. FX-300MF is part of the Carthage [FX[®] High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
☐ Mechanical/Performance/Design Wide Width Tensile Ultimate	ASTM D 4595	52.5 x 47.3 kN/m	3600 x 3240 lbs/ft
Wide Width Tensile @ 5% Strain		21.9 x 22.8 kN/m	1500 x 1560 lbs/ft
☐ Mechanical/Index Grab Tensile Strength	ASTM D 4632	1.780 x 1.335 kN	400 X 300 lbs
Grab Tensile Elongation		10% x 6%	
Trapezoidal Tear	ASTM D 4533	0.601 x 0.556 kN	135 x 125 lbs
CBR Puncture	ASTM D 6241	6.453 kN	1450 lbs
☐ Endurance UV Resistance	ASTM D 4355	80% @ 500 hrs	
☐ Hydraulics/Filtration Permittivity ⁽¹⁾	ASTM D 4491	0.90 sec ⁻¹	
Water Flow Rate ⁽¹⁾		2444 lpm/m ²	60 gpm/ft ²
Apparent Opening Size (AOS) ^(1,2)	ASTM D 4751	0.600 mm	30 US Std. Sieve
☐ Physical Standard Roll Sizes / Packaging / Weight	Measured (Typical)	4.57 m x 91.4 m 418 m ² 147.41 kg	15.0 ft x 300 ft 500 yd ² 325 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

(1) At the time of manufacturing. Handling, storage and shipping may change these properties.

(2) Maximum Average Roll Value

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-2026 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.