



## ■ FX<sup>®</sup>-770MF

Carthage Mills' FX-770MF is a woven High-Performance/High-Strength geotextile produced from high-tenacity polypropylene yarns. FX-770MF is part of the Carthage [FX<sup>®</sup> High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

| PROPERTY                                                      | TEST METHOD        | DATA                                            |                                                    |
|---------------------------------------------------------------|--------------------|-------------------------------------------------|----------------------------------------------------|
|                                                               |                    | METRIC                                          | ENGLISH                                            |
| <input type="checkbox"/> <b>Mechanical/Performance/Design</b> |                    |                                                 |                                                    |
| Wide Width Tensile Ultimate                                   | ASTM D 4595        | 105.1 x 84.0 kN/m                               | 7200 x 5760 lbs/ft                                 |
| Wide Width Tensile @ 5% Strain                                |                    | 52.5 x 52.5 kN/m                                | 3600 x 3600 lbs/ft                                 |
| Grab Tensile Strength                                         | ASTM D 4632        | 2.670 x 2.225 kN                                | 600 x 500 lbs                                      |
| Grab Tensile Elongation                                       |                    | 12 x 6 %                                        |                                                    |
| Trapezoidal Tear                                              | ASTM D 4533        | 1.113 x 0.890 kN                                | 250 x 200                                          |
| CBR Puncture                                                  | ASTM D 6241        | 8.455 kN                                        | 1900 lbs                                           |
| <input type="checkbox"/> <b>Endurance</b>                     |                    |                                                 |                                                    |
| UV Resistance                                                 | ASTM D 4355        | 80% @ 500 hrs                                   |                                                    |
| <input type="checkbox"/> <b>Hydraulics/Filtration</b>         |                    |                                                 |                                                    |
| Permittivity <sup>(1)</sup>                                   | ASTM D 4491        | 0.90 sec <sup>-1</sup>                          |                                                    |
| Water Flow Rate <sup>(1)</sup>                                |                    | 2648 lpm/m <sup>2</sup>                         | 65 gpm/ft <sup>2</sup>                             |
| Apparent Opening Size (AOS) <sup>(1,2)</sup>                  | ASTM D 4751        | 0.85 mm                                         | 20 US Std. Sieve                                   |
| <input type="checkbox"/> <b>Physical</b>                      |                    |                                                 |                                                    |
| Standard Roll Sizes / Packaging / Weight                      | Measured (Typical) | 4.57 m x 91.4 m<br>418 m <sup>2</sup><br>263 kg | 15.0 ft x 300 ft<br>500 yd <sup>2</sup><br>580 lbs |

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- (1) At the time of manufacturing. Handling, storage and shipping may change these properties.  
(2) Maximum Average Roll Value
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
  - The properties reported above are effective 01-01-2026 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.