



■ FX[®]-80HS

Carthage Mills' FX-80HS is a multipurpose nonwoven geotextile made of polypropylene staple fibers which are formed into a random network, needlepunched and heatset for dimensional stability. FX-80HS is part of the Carthage [FX-HS Series](#) of nonwoven geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

AASHTO M 288: FX-80HS exceeds the geotextile requirements for SEPARATION/CLASS 1 (NONWOVEN), STABILIZATION/CLASS 1 (NONWOVEN) and PERMANENT EROSION CONTROL/CLASS 1 (NONWOVEN – ALL SOIL TYPES).

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
☐ Mechanical			
Grab Tensile Strength	ASTM D 4632	0.91 kN	205 lbs
Grab Tensile Elongation		50%	
Trapezoidal Tear	ASTM D 4533	0.36 kN	80 lbs
CBR Puncture	ASTM D 6241	2.23 kN	500 lbs
☐ Endurance			
UV Resistance	ASTM D 4355	70% @ 500 hrs	
☐ Hydraulics / Filtration			
Permittivity ⁽¹⁾	ASTM D 4491	1.4 sec ⁻¹	
Water Flow Rate ⁽¹⁾		3870 lpm/m ²	95 gpm/ft ²
Apparent Opening Size (AOS) ^(1,2)	ASTM D 4751	0.180 mm	80 US Std. Sieve
☐ Physical			
Mass Per Unit Area (Typical)	ASTM D 5261	271.2 g/m ²	8.0 oz/yd ²
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	3.81 m x 109.7 m 418 m ² 121 kg	12.5 ft x 360 ft 500 yd ² 266 lbs
		4.57 m x 91.5 m 418 m ² 115 kg	15.0 ft x 300 ft 500 yd ² 254 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- (1) At the time of manufacturing. Handling, storage and shipping may change these properties.
(2) Maximum Average Roll Value
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 01-01-26 and are subject to change without notice.

» [AASHTO M 288: Geotextile Product Selection Guide](#)

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.