

BENTOMAT® 600CL

GEOSYNTHETIC CLAY LINER

DESCRIPTION

BENTOMAT 600CL GCL is a reinforced geosynthetic clay liner (GCL) consisting of a layer of sodium bentonite between a polypropylene woven geotextile and a polypropylene nonwoven geotextile, which are needlepunched together and laminated to a polyethylene geofilm.



TESTING DATA

CHEMICAL & PHYSICAL PROPERTIES			
MATERIAL PROPERTY	TEST METHOD	TEST FREQUENCY	CERTIFIED VALUES
Bentonite Swell Index ²	ASTM D5890	1 per 50 tonnes	24 mL/2g min.
Bentonite Fluid Loss ²	ASTM D5891	1 per 50 tonnes	18 mL max.
Bentonite Mass/Area ³	ASTM D5993	40,000 ft ² (4,000 m ²)	0.75 lb/ft ² (3.7 kg/m ²) min.
Geofilm Density ¹	ASTM D1505	200,000 ft ² (20,000 m ²)	0.92 g/cm ³
Geofilm Thickness ¹	ASTM D5199	200,000 ft ² (20,000 m ²)	5 mil (0.12 mm) min.
Geofilm Break Strength ^{1,4}	ASTM D882	200,000 ft ² (20,000 m ²)	14 lbs/in (2.5 kN/m) min.
GCL Grab Strength ⁵	ASTM D6768	200,000 ft ² (20,000 m ²)	30 lbs/in (5.3 kN/m) min.
GCL Peel Strength	ASTM D6496	40,000 ft ² (4,000 m ²)	1.0 lbs/in (175 N/m) min.
GCL Hydraulic Conductivity ⁶	ASTM D5887 mod.	Periodic ⁷	5 x 10 ⁻¹⁰ cm/s max.
GCL Index Flux ⁶	ASTM D5887 mod.	Periodic ⁷	1 x 10 ⁻⁹ m ³ /m ² /s max.
GCL Hydrated Internal Shear Strength ⁸	ASTM D6243	Periodic ⁷	150 psf (7.2 kPa) typ. @ 200 psf (9.6 kPa)
Geofilm Durability ^{1,9}	GRI-GCL3 § 5.6.4	Yearly ¹⁰	80% retained min.

Notes:

¹ Geosynthetic property tests performed on the geosynthetic components before they are incorporated into the finished GCL product.

² Bentonite property tests performed before the bentonite is incorporated into the finished GCL product.

³ Reported at 0% moisture content.

⁴ Geofilm tensile break strength performed in the machine and cross-machine directions using ASTM D882.

⁵ GCL tensile strength testing is performed in the machine direction using ASTM D6768.

⁶ ASTM D5887 is modified to include the laminated thin flexible membrane on the test specimen. Index flux and hydraulic conductivity testing with deaired distilled/deionized water at 80 psi (550 kPa) cell pressure, 77 psi (530 kPa) headwater pressure and 75 psi (515 kPa) tailwater pressure. ASTM D5887 (modified) testing is performed only on a periodic basis because the thin flexible membrane is essentially impermeable. The BENTOMAT GCL core (without the flexible membrane) has a maximum hydraulic conductivity of a 5 x 10⁻¹¹ m/s with deaired distilled/deionized water. For more information, see CETCO Technical Reference Nos. 111 and 112.

⁷ Periodic test results can be provided upon request.

⁸ Peak values measured at 200 psf (9.6 kPa) normal stress for a specimen hydrated for 48 hours. Site-specific materials, GCL products, and test conditions must be used to verify internal and interface strength of the proposed design.

⁹ Geofilm test specimens are oven-aged for 50 days at 60°C prior to testing for tensile strength in accordance with paragraph 5.6.4 of GRI-GCL3, rev. 5, dated 11/21/2019.

¹⁰ Yearly testing results can be provided upon request.

cetco.com | cetco@mineralstech.com | 800.527.9948

© 2020 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.cetco.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

technical-data-sheet-bentomat-600cl-gcl-na-en-202012-v1



CETCO®