



# T1000 Non Woven GeoTextile Membrane

## Technical Specification

The T1000 range of Staple Fibre Needle Punched and Thermally Bonded Nonwoven Geotextiles have been designed to offer optimum performance per unit weight. Their resulting mechanical robustness and excellent hydraulic properties make them the ideal choice for separation and filtration. Produced on state of the art equipment, the T1000 geotextile range sets standards in terms of quality and mechanical performance.

Typical applications for TNW thermally bonded non woven geotextiles include:



### Typical Uses and Applications:

- As a general purpose separator for use under site access roads and areas of hard standing
- As a separation and strengthening layer under new roadways, car parks, industrial units etc.
- As a filter surround in the construction of a French drain or granular drainage blanket
- For separation: to prevent the intermixing of dissimilar soil layers
- For filtration: to allow the passage of fluids whilst preventing the uncontrolled passage of soil

| Properties                    | Test Method   | Unit   | T1000    |
|-------------------------------|---------------|--------|----------|
| Tensile Strength - MD         | EN ISO 10319  | kN/m   | 8.4      |
| Tensile Strength - XD         | EN ISO 10319  | kN/m   | 9.8      |
| Elongation at Break - MD      | EN ISO 10319  | %      | 85.0     |
| Elongation at Break - XD      | EN ISO 10319  | %      | 60.0     |
| CBR Puncture Resistance       | EN ISO 10319  | N      | 1500     |
| Dynamic Core Drop             | EN ISO 10319  | Mm     | 25.0     |
|                               |               |        |          |
| Hydraulic Properties          | Test Method   | Units  | T1000    |
| Characteristics Opening size  | EN ISO 10319  | UM     | 110.0    |
| Permeability                  | EN ISO 10319  | m/s    | 110x103  |
| Waterflow normal to the plane | EN ISO 10319  | l/m2.s | 120      |
|                               |               |        |          |
| Physical Properties           | Test Method   | Units  | T1000    |
| Thickness Under 2kPa          | EN ISO 9863-1 | mm     | 0.85     |
| Weight                        | EN ISO 9864   | g/m2   | 115      |
| Roll Size                     |               | m      | 4.5x100m |
| Roll Diameter (+/- 10%)       |               | cm     | 30       |

The information contained herein is, to the best of our knowledge, accurate in all material respects. However, since the circumstances and conditions in which such information and the products mentioned herein can be used may vary and are beyond our control, no representation or warranty, express or implied, of any nature whatsoever is or will be made and no responsibility or liability is or will be accepted by us, any of our affiliates or our or their respective directors, officers, employees or agents in relation to the accuracy or completeness or use of the information contained herein or any such products and any such liability is expressly disclaimed. As part of our continual improvement process GCL Products Ltd reserve the right to change the properties listed on this data sheet without prior notice.