

MACTEX® MXW13 Woven (Stabilization) Geotextile

Maccaferri MacTex® MXW13 geotextile is composed of high tenacity polypropylene yarns, woven into a stable network such that the yarns retain their relative position. MacTex® MXW13 is inert to biological degradation and resists naturally encountered chemicals, alkalis and acids. MacTex® MXW13 conforms to the property values listed below.

PROPERTY	TEST PROCEDURE	UNITS	MINIMUM AVERAGE ROLL VALUES (MARV)
Mechanical			
Grab Tensile	ASTM D 4632	lb (kN)	315 (1.401)
Grab Elongation	ASTM D 4632	%	15
Puncture	ASTM D 4833	lb (kN)	120 (0.533)
Puncture (CBR)	ASTM D 6241	lb (kN)	1000 (4.450)
Trapezoidal Tear	ASTM D 4533	lb (kN)	115 (0.512)
Endurance			
UV Resistance	ASTM D 4355	% Retained @ 500 hrs	70
Hydraulic			
Apparent Opening Size (AOS)	ASTM D 4751	US Sieve (mm)	40 (0.425)
Permittivity	ASTM D 4491	sec ⁻¹	0.05
Flow Rate	ASTM D 4491	gpm/ft ² (lpm/m ²)	4 (160)
Physical (Typical)			
Mass/Weight	ASTM D 5261	oz/yd ² (g/m ²)	6.3 (214)
Packaging (Typical)			
Roll Width	Measured	ft (m)	12.5 (3.81) / 15 (4.57) / 17.5 (5.33)
Roll Length	Measured	ft (m)	432 (131.67) / 360 (109.73) / 309 (94.18) / 300 (91.5) / 258 (78.6)
Roll Area	Measured	yd ² (m ²)	500 (418) / 600 (501)
Roll Weight	Measured	lb (kg)	245 (111) / 270 (123)
Notes: All values are MARV unless otherwise noted. AOS (ASTM D 4751) is a Maximum Opening Diameter Value.			

Maccaferri assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Maccaferri disclaims any and all expressed, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty. This document should not be construed as engineering advice. Maccaferri reserves the right to amend product property values without notice and specifiers are requested to check as to the validity of the specifications they are using. (MacTex® MXW13).



website: www.maccaferri-usa.com

Headquarters:

10303 Governor Lane Boulevard
Williamsport, MD 21795-3116
Tel: 301-223-6910
Fax: 301-223-6134
email: hdqtrs@maccaferri-usa.com

Area Offices:

AZ, Phoenix	MD, Williamsport	OH, Westerville
CA, Sacramento	MO, St. Louis	PR, Caguas
FL, Coral Gables	NJ, Ramsey	TN, Chattanooga
KY, Lexington	NM, Albuquerque	TX, Lewisville