

MACTEX[®] HT

NEEDLEPUNCHED & THERMOCALENDERED NONWOVEN GEOTEXTILES

MacTex [®] HT		500	1000
Mechanical Properties			
Tensile strength — CMD according to EN ISO 10319	kN/m	6 (-0.6)	8 (-0.8)
Strain — CMD according to EN ISO 10319	%	60 (±20)	60 (±20)
Tensile strength — MD according to EN ISO 10319	kN/m	6 (-0.6)	8(-0.8)
Strain — MD according to EN ISO 10319	%	60 (±20)	60 (±20)
CBR Static puncture resistance according to EN ISO 12236	N	1050 (-105)	1500 (-150)
Dynamic perforation resistance according to EN ISO 13433	mm	42 (+8)	38 (+6)
Water flow (normal to the plane) according to EN ISO 11058	m/s	100x10 ⁻³ (-30x10 ⁻³)	90x10 ⁻³ (-27x10 ⁻³)
Opening Pore size O ₉₀ according to EN ISO 12956	µm	95 (±20)	90 (±20)
Physical Properties			
Polymer raw material		100 % Polypropylene	
Roll length	m	100	100
Roll width	m	4.5	4.5
Roll weight	kg	65	60
Durability (to be covered within one month of installation and in natural soils with 4<pH<9 and soil tempetaures <25°C)		100 years	



NOTE:

- Loading plan by truck and container are available on request.
- These data are statistical figures according to Harmonised European Standards.

Nonwoven geotextiles manufactured with virgin polypropylene fibres assembled by a needlepunched treatment and thermocaleandered.

The geotextiles are CE marked according to EN 13249, 13250, 13251, 13252, 13253, 13254, 13255, 13256, 13257, 13265 for the following intended uses: F, S, F+S

For the optimisation and improvement of the technical characteristics of the products, the producer reserves the right to modify the standards and characteristics of the product without warning. The information contained herein is to the best of our knowledge accurate, but since the circumstances and conditions in which it may be used are beyond our control, we do not accept any liability for any loss or damage, however arising, which results directly or indirectly from the use of such information nor do we offer any warranty or immunity against patent infringement. Specifiers are requested to check the validity of the specification they are using.

Maccaferri Ltd:
T: (+44) 1865 770555 www.maccaferri.com/uk
Rep of Ireland:
T: (+353) 18851662 www.geostrong.net

Specialist areas:

Sales:
Technical:
Construction:

E: sales.uk@maccaferri.com
E: technical.uk@maccaferri.com
E: construction.uk@maccaferri.com

