

PRODUCT SPECIFICATIONS

Nilex Nonwoven 4512E

Property	Test	Unit	Value
Mechanical			
Grab Tensile Strength	ASTM-D4632	N (lb)	1424 (320)
Grab Elongation	ASTM-D4632	%	50
Puncture Strength	ASTM-D4833	N (lb)	934 (210)
CBR Puncture	ASTM-D6241	N (lb)	4115 (925)
Mullen Burst	ASTM-D3786	kPa (psi)	4274 (620)
Trapezoid Tear	ASTM-D4533	N (lb)	556 (125)
Hydraulic			
Apparent Opening Size	ASTM-D4751	mm (US Sieve)	0.150 (100)
Permittivity	ASTM-D4491	sec ⁻¹	0.80
Permeability	ASTM-D4491	cm/sec	0.29
Water Flow Rate	ASTM-D4491	l/m/m ² (gpm/ft ²)	2445 (60)
Physical			
Mass Per Unit Area	ASTM-D5261	g/m ² (oz/yd ²)	407 (12)
Thickness	ASTM-D5199	mm (mils)	2.9 (115)
Endurance			
UV Resistance	ASTM-D4355	% @ 500 hrs	70

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.



ROADS



EROSION &
SEDIMENT CONTROL



DRAINAGE



CONTAINMENT

nilex.com