

PRODUCT SPECIFICATIONS

Nilex Nonwoven Civil Geotextile Comparison



Minimum Average Roll Values (MARV)

Property	Test	Unit	Nilex 4504 (White)	Nilex 4510	Nilex 4512	Nilex 4516	Nilex 4535	Nilex 4545	Nilex 4546	Nilex 4547	Nilex 4551	Nilex 4552	Nilex 4553
Mechanical													
<u>Grab Tensile Strength</u>	ASTM D-4632	N (lb)	445 (100)	1112 (250)	1334 (300)	1690 (380)	356 (80)	400 (90)	534 (120)	445 (100)	712 (160)	801 (180)	912 (205)
<u>Grab Elongation</u>	ASTM D-4632	%	50	50	50	50	50	50	50	50	50	50	50
<u>CBR Puncture*</u>	ASTM D-6241	N (lb)	---	3114 (700)	3781 (850)	4804 (1080)	934 (210)	1157 (260)	1379 (310)	1334 (300)	1824 (410)	2113 (475)	2335 (525)
<u>Trapezoidal Tear</u>	ASTM D-4533	N (lb)	222 (50)	445 (100)	512 (115)	645 (145)	133 (30)	178 (40)	222 (50)	222 (50)	267 (60)	334 (75)	356 (80)
Hydraulic													
<u>Apparent Opening Size</u>	ASTM D-4751	mm (US Sieve)	0.212 (#70)	0.150 (#100)	0.150 (#100)	0.150 (#100)	0.300 (#50)	0.250 (#60)	0.212 (#70)	0.212 (#70)	0.212 (#70)	0.212 (#70)	0.180 (#80)
<u>Permittivity</u>	ASTM D-4491	sec ⁻¹	2	1.2	1.0	0.7	2.2	2.0	1.7	2.0	1.5	1.4	1.5
<u>Water Flow Rate</u>	ASTM D-4491	l/m/m ² (gpm/ft ²)	5689 (140)	3260 (80)	3056 (75)	2037 (50)	6112 (150)	6112 (150)	5704 (140)	5704 (140)	4482 (110)	4278 (105)	4482 (110)
Endurance													
<u>UV Resistance</u>	ASTM D-4355	% @ 500 hrs	70	70	70	70	70	70	70	70	70	70	70
Packaging													
<u>Roll Size</u>	Measured	m (ft)	5.40 x 100 (17.7 x 328)	4.57 x 91.5 (15 x 300)	4.57 x 91.5 (15 x 300)	4.57 x 91.5 (15 x 300)	3.81 x 109.8 (12.5 x 360) 4.57 x 109.8 (15 x 360)	3.81 x 109.8 (12.5 x 360) 4.57 x 109.8 (15 x 360)	3.81 x 109.8 (12.5 x 360) 4.57 x 109.8 (15 x 360)	3.81 x 109.8 (12.5 x 360) 4.57 x 109.8 (15 x 360)	3.81 x 109.8 (12.5 x 360) 4.57 x 91.5 (15 x 300)	3.81 x 109.8 (12.5 x 360) 4.57 x 91.5 (15 x 300)	3.81 x 109.8 (12.5 x 360) 4.57 x 91.5 (15 x 300)

*Note: Mullen Burst ASTM D3786 and Puncture Strength ASTM D4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.