

PRODUCT SPECIFICATIONS

Nilex Woven Geotextile

Minimum Average Roll Values (MARV)

PROPERTY	TEST	UNIT	Nilex 2002	Nilex 2004	Nilex 2006
Mechanical					
<u>Grab Tensile Strength</u>	ASTM-D4632	N (lb)	890 (200)	1110 (250)	1400 (315)
Grab Elongation	ASTM-D4632	%	12	12	12
<u>Puncture Strength</u>	ASTM-D4833	N (lb)	400 (90)	489 (110)	667 (150)
<u>CBR Puncture*</u>	<u>ASTM-D6241</u>	N (lb)	3110 (700)	3335 (750)	4000 (900)
<u>Mullen Burst</u>	ASTM-D3786	kPa (psi)	2578 (400)	3447 (500)	4137 (600)
<u>Trapezoidal Tear</u>	ASTM-D4533	N (lb)	330 (75)	400 (90)	533 (120)
Hydraulic					
<u>Apparent Opening Size</u>	ASTM-D4751	mm (US Sieve)	0.425 (40)	0.425 (40)	0.425 (40)
<u>Permittivity</u>	ASTM-D4491	sec ⁻¹	0.05	0.05	0.05
<u>Water Flow Rate</u>	ASTM-D4491	l/m/m ² (gpm/ft ²)	160 (4)	160 (4)	160 (4)
Endurance					
<u>UV Resistance</u>	ASTM-D4355	% @ 500 hrs	70	70	70
Packaging					
<u>Roll Width</u>	Measured	m (ft)	3.81 (12.5) 4.57 (15) 5.33 (17.5)	3.81 (12.5) 5.33 (17.5)	3.81 (12.5) 5.33 (17.5) 4.57 (15) 5.33 (17.5)
<u>Roll Length</u>	Measured	m (ft)	131.7 (432) 109.8 (360) 94.2 (309)	109.8 (360) 78.6 (258)	109.8 (360) 120 (394) 91.5 (300) 78.6 (258)

*Note: Mullen Burst ASTM D3786 and Puncture Strength ASTM D4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.