



**GEOTEX 104F** is a woven monofilament polypropylene geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that filaments retain dimensional stability relative to each other. These characteristics make **GEOTEX 104F** ideal for filtration beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 104F** conforms to the property values listed below.<sup>1</sup> Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved for AASHTO standards.

MARV<sup>2</sup>

| PROPERTY                                 | TEST METHOD                | ENGLISH                         | METRIC                             |
|------------------------------------------|----------------------------|---------------------------------|------------------------------------|
| <b>ORIGIN OF MATERIALS</b>               |                            |                                 |                                    |
| % U.S. Manufactured Inputs               |                            | 100%                            | 100%                               |
| % U.S. Manufactured                      |                            | 100%                            | 100%                               |
| <b>MECHANICAL</b>                        |                            |                                 |                                    |
| Tensile Strength (Grab)                  | ASTM D-4632                | 370 x 250 lbs                   | 1,647 x 1113 N                     |
| Elongation                               | ASTM D-4632                | 15 x 15%                        | 15 x 15%                           |
| CBR Puncture                             | ASTM D-6241                | 950 lbs                         | 4228 N                             |
| Trapezoidal Tear                         | ASTM D-4533                | 100 x 60 lbs                    | 445 x 267 N                        |
| <b>ENDURANCE</b>                         |                            |                                 |                                    |
| UV Resistance<br>% Retained at 500 hrs   | ASTM D-4355                | 90%                             | 90%                                |
| <b>HYDRAULIC</b>                         |                            |                                 |                                    |
| Apparent Opening Size (AOS) <sup>3</sup> | ASTM D-4751                | 70 US Std. Sieve                | 0.212 mm                           |
| Percent Open Area                        | CW-02215 MOD. <sup>4</sup> | 4-6 %                           | 4-6 %                              |
| Permittivity                             | ASTM D-4491                | 0.28 sec <sup>-1</sup>          | 0.28 sec <sup>-1</sup>             |
| Water Flow Rate                          | ASTM D-4491                | 18 gpm/ft <sup>2</sup>          | 733 lpm/m <sup>2</sup>             |
| <b>ROLL SIZES</b>                        |                            |                                 |                                    |
|                                          |                            | 6 ft x 300 ft<br>12 ft x 300 ft | 1.83 m x 91.5 m<br>3.66 m x 91.5 m |

**NOTES:**

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.
4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)



TESTED. PROVEN. TRUSTED.  
[www.geotextile.com](http://www.geotextile.com)

**Propex Operating Company, LLC** · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422

ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex<sup>®</sup>, Landlok<sup>®</sup>, Pyramat<sup>®</sup>, X3<sup>®</sup>, SuperGro<sup>®</sup>, Petromat<sup>®</sup> and Petrotac<sup>®</sup> are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.

© 2011 Propex Operating Company, LLC