

GEOTEX® 111F is a woven monofilament polypropylene geotextile and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that the filaments retain dimensional stability relative to each other. These characteristics make GEOTEX® 111F ideal for filtration applications beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 111F conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP tested for AASHTO standards.

| MARV <sup>2</sup>                        |                            |                         |                           |
|------------------------------------------|----------------------------|-------------------------|---------------------------|
| PROPERTY                                 | TEST METHOD                | ENGLISH                 | METRIC                    |
| <b>ORIGIN OF MATERIALS</b>               |                            |                         |                           |
| % U.S. Manufactured                      |                            | 100%                    | 100%                      |
| <b>MECHANICAL</b>                        |                            |                         |                           |
| Grab Tensile Strength                    | ASTM D-4632                | 365 x 200 lbs           | 1624 x 890 N              |
| Grab Elongation                          | ASTM D-4632                | 24 x 10 %               | 24 x 10 %                 |
| CBR Puncture                             | ASTM D-6241                | 675 lbs                 | 3003 N                    |
| Trapezoidal Tear                         | ASTM D-4533                | 115 x 75 lbs            | 512 x 334 N               |
| <b>ENDURANCE</b>                         |                            |                         |                           |
| UV Resistance at 500 hrs                 | ASTM D-4355                | 90%                     | 90%                       |
| <b>HYDRAULIC</b>                         |                            |                         |                           |
| Apparent Opening Size (AOS) <sup>3</sup> | ASTM D-4751                | 40 US Std. Sieve        | 0.425 mm                  |
| Percent Open Area                        | CW-02215 MOD. <sup>4</sup> | 10%                     | 10%                       |
| Permittivity                             | ASTM D-4491                | 2.10 sec <sup>-1</sup>  | 2.10 sec <sup>-1</sup>    |
| Water Flow Rate                          | ASTM D-4491                | 145 gpm/ft <sup>2</sup> | 5908 l/min/m <sup>2</sup> |
| <b>ROLL SIZES<sup>5</sup></b>            |                            | 12.5 ft x 300 ft        | 3.81 m x 91.5 m           |

### NOTES:

1. The property values listed above are effective 12/17/2018 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
3. Maximum average roll value.
4. 4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)
5. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.