

GEOTEX® 1291 is a polypropylene, staple fiber, needle-punched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needed to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 1291 conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP tested for AASHTO standards.

MARV ²			
PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area	ASTM D-5261	12.0 oz/yd ²	407 g/m ²
Thickness	ASTM D-5199	115 mils	2.9 mm
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	320 lbs	1423 N
Grab Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	925 lbs	4115 N
Trapezoidal Tear	ASTM D-4533	125 lbs	556 N
ENDURANCE			
UV Resistance at 500 hrs	ASTM D-4355	70%	70%
HYDRAULIC			
Apparent Opening Size (AOS) ³	ASTM D-4751	100 US Std. Sieve	0.150 mm
Permittivity	ASTM D-4491	0.9 sec ⁻¹	0.9 sec ⁻¹
Permeability	ASTM D-4491	0.30 cm/sec	0.30 cm/sec
Water Flow Rate	ASTM D-4491	65 gpm/ft ²	2648 l/min/m ²
ROLL SIZES ⁴		15 ft x 300 ft	4.57 m x 91.5 m

NOTES:

- The property values listed above are effective 09/16/2016 and are subject to change without notice.
- Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
- Maximum average roll value.
- Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.