

ProPex[®] Woven Geotextiles

PROPERTIES¹	TEST METHOD	UNITS	1198		1199		2000		2002			2004		2006			2016	2019	2044	
PHYSICAL																				
Grab Tensile Strength²	ASTM D 4632	lb	300/200		370/250		140		200			250		315			315	350/250		600/500
Grab Tensile Elongation²	ASTM D 4632	%	15		16		15		15			15		15					15	
Wide Width Tensile	ASTM D 4595	lb/ft	N/A		N/A		N/A		N/A			N/A		2100			2400	N/A		4800
Wide Width Elongation²	ASTM D 4595	%	N/A		N/A		N/A		N/A			N/A		15/8			12/8	N/A		10/8
Mullen Burst	ASTM D 3786	psi	450		480		325		400			500		600					1350	
Puncture	ASTM D 4833	lb	120		120		65		95			110		145			140	140	180	
Trapezoid Tear	ASTM D 4533	lb	65		100/60		55		75			90		120			125	100	250	
UV Resistance³	ASTM D 4355	% @ _hr	90@500		90@500		70@500		70@500			70@500		70@500			80@500	90@500	80@500	
HYDRAULIC																				
Apparent Opening Size (AOS)⁵	ASTM D 4751	US Sieve	40		70		30		40			40		40			40	70	30	
Permittivity	ASTM D 4491	sec⁻¹	0.50		0.28		0.05		0.05			0.05		0.05			0.70	0.28	0.15	
Flow Rate	ASTM D 4491	gal/min/ft²	35		18		4		4			4		4			50	18	10	
PACKAGING																				
Roll Width		ft	6.25	12	6	12	12.5	17.5	12.5	15	17.5	12.5	17.5	12.5	15	17.5	15	15	12.5	15
Roll Length		ft	634	330	450	225	504	360	504	420	360	360	258	360	300	258	300	300	216	180
Gross Weight⁴		lb	205		150		180		250			248		272			260	262	293	
Area		yd²	440		300		700	700	700	700	700	500	501	500	500	501	500	500	300	
SUGGESTED APPLICATIONS																				
Separation							X		X			X		X			X		X	
Stabilization									X			X		X			X		X	
Reinforcement														X			X		X	
Erosion Control/Drainage			X		X												X	X		
MINIMUM AVERAGE ROLL VALUES																				

N/A -Not Applicable

1. Physical and hydraulic properties reported as minimum average roll values (MARV).

2. Machine direction / cross-machine direction.

3. Percent grab tensile strength retained per hours of UV exposure following conditioning in accordance with ASTM-D-4355.

4. Gross weights are approximate.

5. AOS reported as maximum average value.

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.



