

DATA SHEET

BLANKET FOR EROSION CONTROL - WOOD FIBERS (SINGLE NETTING)

PRODUCT DESCRIPTION: Blanket composed of a mixture of poplar wood fibers of which 80% of the fibers are 150 mm (6 in) long or more. The top is covered with green oxo-biodegradable polypropylene netting and contains UV additives.

FUNCTION: Control

RAW MATERIAL: Poplar wood fibers and polypropylene mesh

TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Thickness	ASTM D6525	10.44 mm	0.411 in
	Mass per unit area	ASTM D6475	309 g/m ²	0.06 lb/ft ²
	Resiliency	ASTM D1117/ECTC	59.0 %	
	Light penetration	ASTM D6567	20.5 %	
MECHANICAL	Tensile strength MD	ASTM D6818	1.14 kN/m	78.0 lb/ft
	Tensile strength TD	ASTM D6818	0.54 kN/m	37.2 lb/ft
	Elongation at break MD	ASTM D6818	20.3 %	
	Elongation at break TD	ASTM D6818	14.3 %	
PERFORMANCE AND DURABILITY	Functional longevity ⁽⁴⁾	-	≤ 18 months	
OTHER	Swelling	ECTC procedure	49.0 %	
	Water absorbency	ASTM D1117/ECTC	253.0 %	
	Laboratory testing of rain splash	ASTM D7101	SLR = 4.12 @ 2 in/hr ^(2,3)	
			SLR = 4.43 @ 4 in/hr ^(2,3)	
			SLR = 4.79 @ 6 in/hr ^(2,3)	
	Shear test	ASTM D7207	2.32 lb/ft ² @ 0.5 in of soil loss	
DIMENSIONS AND WEIGHT	Germination improvement	ASTM D7322	572.0 %	
	Width	-	2.44 m	8.0 ft
	Length	-	34.29 m	112.5 ft
	Surface	-	83.67 m ²	900.0 ft ²
	Weight (± 10 %)	-	33.1 kg	73.0 lb
	Mesh opening	-	25.4 mm x 50.8 mm	1.0 in x 2.0 in

Note 1: Weight is based on dry fibre. During its manufacture, the reference humidity level for wood fibers is 22 %.

Note 2: SLR is the soil leach ratio, as defined by NTPEP/AASHTO.

Note 3: The laboratory tests indexes should not be used for design purposes.

Note 4: Functional longevity varies from region to region because of differences in climatic conditions.

The enclosed information is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5 % from standard sizes.

Soleno Textile Inc. offers no guarantee regarding the use, installation or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractual warranty.

DATA SHEET

BLANKET FOR EROSION CONTROL - WOOD FIBERS (SINGLE NETTING) (CONT.)

Wood mats are designed to channel a flow rate up to 2.1 m/s (7.0 ft/s) and 84 N/m² (1.75 lbs/ft²) of shear stress limit.

Wood mats have a rate of soil loss of 0.018 and are generally appropriate for slopes up 2H:1V.

APPLICATIONS: Retaining walls and embankments
Grow vegetation areas