

DATA SHEET

TEXGUARD

PRODUCT DESCRIPTION : Sediment barrier

FUNCTION : Protection

COMPLIANCE : A mesure allowing for the acquisition of LEED points® from the Canada Green Building Council, Sustainable Sites.

RAW MATERIAL : Polypropylene

TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
MECHANICAL	Tensile strength	ASTM D4632	445 N x 445 N	100 lb x 100 lb
	Elongation at break	ASTM D4632	min. 15 %	
	Tear strength	ASTM D4533	50 N x 50 N	322 lb x 322 lb
	CBR Puncture resistance	ASTM D6241	1112 N	250 lb
HYDRAULIC	Flow rate	ASTM D4491	326 l/min/m ²	8 gpm/ft ²
	Permittivity	ASTM D4491	0.1 s ⁻¹	
	Apparent opening size (AOS) ⁽¹⁾	ASTM D4751	0,600 mm	30 US Std. Sieve
PERFORMANCE AND DURABILITY	UV resistance (500 hours)	ASTM D4355	80 %	
DIMENSIONS	Standard width	-	0,91 m	3 ft
	Standard length	-	30,48 m	100 ft
	With stakes at every:	-	3 m	9,84 ft

Note 1: Maximum average roll value

The enclosed information is provided at no cost or obligation on the part of Soleno Textiles Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textiles Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5 % from standard sizes.

Soleno Textiles Inc. offers no guarantee regarding the use, installation or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textiles Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textiles Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textiles Inc.'s liability will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractual warranty.

APPLICATIONS : Retention of sediments