



**Tel:** 800-752-9326  
**Fax:** 763-389-2725  
**SRWProducts.com**

PO Box 70  
32005 126th St  
Princeton, MN 55371

## **SRW NW7**

To Whom It May Concern:

This letter is to certify that SRW Products Manufactures/Supplies a 100% Polypropylene Non-Woven produced by needle punching staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene material is specially formulated to resist ultraviolet light deterioration and is inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. **This Fabric is MADE IN THE USA.**

**SRW NW7** meets or exceeds the physical property values listed below.

| Fabric Property    | Test Method | Units               | Minimum Average Roll Value |
|--------------------|-------------|---------------------|----------------------------|
| Grab Tensile       | ASTM D 4632 | lbs.                | 180 (0.800 kN)             |
| Grab Elongation    | ASTM D 4632 | %                   | 50                         |
| Trap-Tear Strength | ASTM D 4533 | lbs.                | 75 (.333 kN)               |
| CBR Puncture       | ASTM D 6241 | lbs.                | 475 (2.113 kN)             |
| Permittivity       | ASTM D 4491 | sec <sup>-1</sup>   | 1.4                        |
| Water Flow         | ASTM D 4491 | gpm/ft <sup>2</sup> | 105 (4278 l/min/sm)        |
| UV Resistance      | ASTM D 4355 | %                   | 70/500 hrs.                |
| AOS                | ASTM D 4751 | US Sieve            | #70 (.212 mm)              |

Values Provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described. Product packaging will clearly state either SRW NW7 or SR070, verifying that it is NW7 inside.