



GlasGrid® Asphalt Reinforcement System

Specification Sheet – GlasGrid® 8512 TF Asphalt Reinforcement System

Specifications for Use in Asphalt Overlays			
Property	Test Method	8512 TF	
		Metric	Imperial
Tensile Strength (Ultimate) (MD x XD)	ASTM D6637 EN-ISO 10319	100 x 200 kN/m	571 x 1,142 lb/in.
Tensile Elongation (Ultimate)	ASTM D6637 EN-ISO 10319	< 3%	< 3%
Tensile Resistance @ 2% Strain (MD x XD)	ASTM D6637 EN-ISO 10319	80 x 160 kN/m	456 x 913 lb/in.
Young's Modulus E		73,000 MPa	10.6 x 10 ⁶ psi
Mass/Unit Area	ASTM D5261 ISO 9864	637 g/m ²	18.8 oz/yd ²
Melting Point Coating	ASTM D276/EN-ISO 3146	>232° C	>450° F
Melting Point Glass	ASTM C338	>820° C	>1508° F
Roll Length		60 m	197 ft
Roll Width		1.5 m	5 ft
Roll Area		90 m ²	108 yd ²
Adhesive Backing		Pressure Sensitive	
Grid Size (Center to Center of Strand)		25 x 19 mm	1.0 x 0.75 in.
Material	Fiberglass reinforcement with modified polymer coating and pressure-sensitive adhesive backing bonded to polymer tack film		
Film Type		100% Polymer	
Film Softening Point		99°C	210°F

The values and tolerances given are obtained in our laboratories and in accredited testing institutions. All imperial values are approximate. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.

Tensar®

Tensar International Corporation
2500 Northwinds Parkway
Suite 500
Alpharetta, GA 30009
800-TENSAR-1
tensarcorp.com

GlasGrid® is distributed in the United States of America, Canada and certain other countries by Tensar International Corporation (Tensar). Inasmuch as Saint-Gobain ADFORS and Tensar have no control over installation design, installation workmanship, accessory materials, or conditions of application, Saint-Gobain ADFORS and Tensar do not warrant the performance or results of any installation or use of GlasGrid®. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose.

Exclusive distributors in the Americas for:



©2016, Tensar International Corporation

GG_MPDS_8512TF_11.16