

Terrafix 1600E – Protection Geotextile

Function: Filtration, Drainage, Reinforcement & Cushion.

Main function: Protection.

Terrafix 1600E is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. Terrafix 1600E resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2-13.

Types of applications for 1600E are: Heavy Shore-Line Coastal Applications / Abrasion Resistance Requirements / Cushion Requirements / Geomembrane liner protection to avoid punctures in the liner.

Property	ASTM Test Method	Value Metric Units
Typical Geotextile Properties		
• Weight (Typical)	D 5261	545 g / m ² (16 oz/sqyd)
Thickness	D 5199	4.1 mm
• Tensile Strength	D 4632	1891 N
• Trapezoid Tear	D 4533	690 N
• Elongation at break	D 4632	50-105%
• Puncture CBR	D 6241	5340 N
• Permittivity / Permeability	D 4491	0.7 sec ⁻¹ / 0.31 cm/sec
• Water Flow	D 4491	2037 l/min/m ²
• Apparent Opening Size	D 4751	0.150 mm (100 US sieves)
• U.V. Stability	D 4355	70% @ 500hrs

The information contained herein has been compiled by TGI, and is, to the best of our knowledge, true and accurate. This information is offered without warranty. Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice. Terrafix is a registered trademark of Terrafix Geosynthetics Inc. Terrafix 12-2023.

1600E is available in 3.81m or 4.57m or 5.25m wide by 300m in length.