

Terrafix 400W – Woven Geotextile

Function: Reinforcement & Separation

Terrafix 400W woven geotextiles are designed and manufactured for many construction applications. They perform the three primary functions of a geotextile: separation (separating the native subgrade from an aggregate layer); reinforcement (reinforcing an area by distributing weight over a wider area); and filtration (retaining soil while allowing the passage of water). Terrafix 400W woven geotextiles are made of polypropylene filaments that are formed into a stable network such that they retain their relative position.

Types of applications for this textile are:

Roadways, Access Roads, Industrial Yards, Logging Roads.

Property	ASTM Test Method	Value Metric Units
Typical Geotextile Properties		
• Weight (Typical)	D 5261	190 g / m ² (5.6 oz/sqyd)
• Grab Tensile Strength	D 4632	1417 N
• Grab Elongation	D 4632	15%
• Tear Resistance	D 4533	533 N
• Puncture CBR	D 6241	4450 N
• Permittivity ¹	D 4491	0.05 sec ⁻¹ Avg.
• Water Flow ¹	D 4491	163 l/min/m ² Avg.
• Apparent Opening Size ^{1 2}	D 4751	0.425 mm Avg.
• U.V. Stability	D 4355	70% @ 500hrs

The information contained herein has been compiled by TGI Ltd. and is, to the best of our knowledge, true and accurate. This information is offered without warranty. Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice.

Unless noted otherwise, all values are minimum average roll values (MARV).

1- at the time of manufacturing. Handling, storage, and shipping may change these properties. 2- Value represents maximum average roll value.