

Terrafix 800E – Protection Geotextile

Function: Filtration, Drainage, Reinforcement & Cushion.

Main function: Protection.

Terrafix 800E is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. Terrafix 800E resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2-13.

Types of applications for 800E are: Light Coastal Applications / Abrasion Resistance Requirements / Cushion Requirements as well for plastic liners to avoid punctures in a plastic liner such as EPDM, PVC, HDPE.

800E: 24" (inches) maximum rip-rap size / Good abrasion resistance / Medium to high strength at high elongation. Primary purpose of 800E is to act as a cushion geotextile.

Property	ASTM Test Method	Value Metric Units
Typical Geotextile Properties		
• Weight (Typical)	D 5261	340 g / m ² (~10 oz/sqyd)
Thickness	D 5199	2.7mm
• Grab Tensile Strength	D 4632	1200 N
• Tear Resistance	D 4533	470 N
• Grab Elongation	D 4632	50-105%
• Puncture CBR	D 6241	3220 N
• Permittivity / Permeability	D 4491	1.2 sec ⁻¹ / 0.31 cm/sec
• Water Flow	D 4491	3463 l/min/m ²
• Apparent Opening Size	D 4751	0.150 mm
• U.V. Stability	D 4355	70% @ 500hrs

The information contained herein has been compiled by TGI, and is, to the best of our knowledge, true and accurate. This information is offered without warranty. Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice. Terrafix is a registered trademark of Terrafix Geosynthetics Inc. Terrafix 12-2023.

800E is available in 3.81m or 4.57m or 5.25m wide by 300m in length.