

PRODUCT SPECIFICATIONS

Nilex Monofilament Woven Geotextile

Minimum Average Roll Values (MARV)

PROPERTY	TEST	UNIT	Nilex 1198	Nilex 1199
Origin of Materials				
U.S. Manufactured		%	100	100
Mechanical				
Grab Tensile Strength	ASTM-D4632	N (lb)	1624 x 890 (365 x 200)	1646 x 1112 (370 x 250)
Elongation	ASTM-D4632	%	24 x 10	15 x 15
CBR Puncture*	ASTM-D6241	N (lb)	3003 (675)	4226 (950)
Trapezoidal Tear	ASTM-D4533	N (lb)	512 x 334 (115 x 75)	445 x 267 (100 x 60)
Hydraulic				
Percent Open Area	CW-02215 MOD. ⁴	%	10	4
Apparent Opening Size	ASTM-D4751	mm (US Sieve)	0.425 (#40)	0.212 (#70)
Permittivity	ASTM-D4491	sec ⁻¹	2.10	0.28
Water Flow Rate	ASTM-D4491	l/m/m ² (gpm/ft ²)	5908 (145)	733 (18)
Endurance				
UV Resistance	ASTM-D4355	% @ 500 hrs	90	90
Packaging				
Roll Size	Measured	m (ft)	3.81 x 91.5 (12.5 x 300)	1.83 x 91.5 (6 x 300) 3.66 x 91.5 (12 x 300)

*Note: Mullen Burst ASTM D3786 and Puncture Strength ASTM D4833 are no longer recognized by ASTM Committee D35 as an acceptable geotextile test method. Puncture Strength ASTM 4833 has been replaced with the Static (CBR) Puncture ASTM D6241. For more information, refer to the ASTM website at www.astm.org

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.