

PRODUCT SPECIFICATIONS

HLR (Hot Liquid Rated) Series

High Temperature Geomembrane Liners – 60, 80 & 100 mil

PROPERTY	TEST	UNIT	VALUE – 60 mil	VALUE – 80 mil	VALUE – 100 mil
Thickness (min. avg.)	ASTM D-5199	mm (in)	1.5 (0.06)	2.0 (0.08)	2.5 (0.10)
Sheet Density	ASTM D-1505	g/cc (lb/in ³)	0.940 (0.034)	0.940 (0.034)	0.940 (0.034)
Carbon Black Content	ASTM D-4218	%	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Tensile Strength at Break	ASTM D-6693	kN/m (lb/in)	42 (240)	56 (320)	68 (388)
Elongation at Break	ASTM D-6693	%	650	650	650
Tear Resistance	ASTM D-1004	N (lb)	200 (45)	258 (58)	320 (72)
Puncture Resistance	ASTM D-4833	N (lb)	534 (120)	712 (160)	823 (185)
Oven Aging (HP-OIT)	ASTM D-5885	%	90	90	90
UV Resistance (HP-OIT)	ASTM D-5885	%	85	85	85

Disclaimer: The information provided by Nilex is believed to be correct and is generally based on information supplied by the manufacturers of the product offered. Any recommendations made by Nilex concerning uses or applications of our products are also believed to be reliable; however, as Nilex has no control over design execution, and field conditions of the project which incorporate the product. Nilex disclaims all warranties, expressed or implied, including, without limitation, the warranties of merchantability and/or fitness for a particular purpose.